

TITANLUX SYNTHETIC ENAMEL

Indoor - Outdoor. Gloss



Product Code: 001

Description

Synthetic enamel. Based on high solids technology. Quick-drying. Multi-Purpose. High gloss. Elastic. Excellent colour and gloss stability. High resistance to scratching. Good levelling and edge coverage. Resistant to weathering, grease, washes, etc. All its colours are intermixable and the white colour has an extraordinary whiteness and resistance to yellowing.

Fields of Application

For indoor and outdoor use. To protect and embellish doors, furniture, industrial vehicles, machinery, etc.

Technical Data

Product Type	High solid alkyd
Finish	Gloss
Colour (UNE EN ISO 11664-4)	White and colours + TITANCOLOR Bases: W0 White, W1 White and Neutral
Density (UNE EN ISO 2811-1)	White: 1.17-1.19 Kg/l, Black: 0.97-0.99 Kg/l, Colours: 0.96-1.20 Kg/l
Coverage (UNE 48282)	12 -14 m ² /l (45 - 50 μ)
Drying at 23°C 60 % RH (UNE 48301)	4 - 5 hours
Recoat time at 23°C 60% RH (UNE 48283)	18 - 24 hours
Methods of Application	Brush, roller and spray-gun
Equipment Cleaning	Odourless Thinner or White Spirit
Tinting	TITANCOLOR System
Flash Point (UNE EN ISO 3679)	40 - 42 °C
Volume Solids (UNE EN ISO 3233-3)	63 - 65 %
VOC (UNE EN ISO 11890-2)	2.004/42IIA (d) (400/300) Max. VOC 300 gr/l
Pack sizes	566D and 566E White: 4 l, 1 l, 750 ml, 375 ml and 125 ml / Colours: 4 l, 750 ml, 375 ml and 125 ml / TITANCOLOR Bases: 4 l and 750 ml

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Certificates

Reaction to Fire UNE EN 13501-1:2007+A1:2010: B - s1, d0

Directions for use

GENERAL REMARKS:

Stir well before using. The surfaces to be painted have to be clean, dry and suitably primed. Remove all existing rests of dirt, grease, poorly adhered rust and previous coatings by using thinner or paint stripper, depending on requirements.

High-solids paints leave a thicker dry film. They should not be applied at thicknesses in excess of the data recommended in order to avoid problems of drying and surface appearance.

If the temperature of the surface is below 10°C and if paint coat is thick, the overcoating time has to be longer. Check that the surface is suitably dry before overcoating.

BARE SURFACES:

Wood: Sand wood following the wood grain, thoroughly clean, remove all resins or resin secretion on the surface and smooth up sharp edges. Apply TITAN Sealing-Primer or Multi-Purpose Primer depending on requirements.

Iron and steel: TITANLUX Synthetic Rust-Preventive Primer or TITAN Multi-Purpose Primer. For outdoor surfaces, at least two coats of the selected primer will be needed. For indoor surfaces, one coat will be enough.

Other surfaces: Please consult your dealer.

In all cases for:

Indoor surfaces: Finish with 1 or 2 coats of TITANLUX Synthetic Enamel

Outdoor surfaces: Finish with 2 or 3 coats of TITANLUX Synthetic Enamel.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Wash, lightly sand and directly apply 1 or 2 coats of TITANLUX Synthetic Enamel.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Completely remove all previous paint coats and proceed as for bare surfaces.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

Waste management: Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use.

Issue date: 2019-11

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



TITAN

001 - TITANLUX SYNTHETIC ENAMEL

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

