

TITANLAK POLYURETHANE ENAMEL

Indoors - Outdoors. Satin



Product Code: 011

Description

Synthetic enamel. Based on high solids technology. Specially for lacquering and enamelling. Easy application, producing premium quality, fine, soft-feel satin finishes with an excellent lacquered look. Great resistance to wearing, scratching, soaps, liqueur, juice and oil stains. Highly wash-resistant.

Fields of Application

For indoor and outdoor use. For protecting and decorating all kinds of wood and metal surfaces (such as furniture, shelves, doors, windows and radiators).

Technical Data

Product Type	High solid urethaned alkyd
Finish	Satin
Colour (UNE EN ISO 11664-4)	White and colours
Density (UNE EN ISO 2811-1)	White: 1.36 - 1.38 Kg/l, Black: 1.21 - 1.23 Kg/l, Colours: 1.22 - 1.39 Kg/l
Coverage (UNE 48282)	12 - 14 m ² /l (40 - 45μ)
Drying at 23°C 60 % RH (UNE 48301)	4 - 5 hours
Recoat time at 23°C 60% RH (UNE 48283)	18 - 24 hours
Methods of Application	Brush, roller and spray-gun
Equipment Cleaning	Synthetics and Grease Thinner, Odourless Thinner or White Spirit.
Application Temperature, RH<80%	+10°C - +30°C
Flash Point (UNE EN ISO 3679)	40 - 41 °C
Volume Solids (UNE EN ISO 3233-3)	60 - 63 %
VOC (UNE EN ISO 11890-2)	2.004/42/IIA (d) (400/300) Max. COV 300 g/l
Pack sizes	4 l, 2.5 l (only in white), 750 ml, 375 ml and 125 ml.

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Certificates

TITAN Multi-Purpose Primer (code 06A) and TITANLAK Polyurethane Enamel (code 011) are classed B-s1, d0 concerning their Reaction to Fire according to UNE EN 13501-1:2007+A1:2010, always on condition that they are applied together, as primer plus topcoat system and on A1 compliant materials.

Directions for use

GENERAL REMARKS:

Stir well before using. The surfaces to be painted have to be clean, dry and suitably primed.

Remove all existing rests of dirt, grease, poorly adhered rust and previous coatings by using thinner or paint stripper, depending on requirements.

High-solids paints leave a thicker dry film. They must not be applied at thicknesses in excess of the data recommended in order to avoid problems of drying and surface appearance.

If it is required to modify the satin grade of our TITANLAK Enamel, we advise to mix it with TITANLUX Matt Enamel or Gloss Enamel, depending on needs.

For outdoor application, we do not recommend any mixtures with TITANLUX Matt Enamel.

If the temperature of the surface is below 10°C and if paint coat is thick, the overcoating time has to be longer. Check that the surface is suitably dry before overcoating.

IMPORTANT: It reaches its final satin appearance after 3 days approx. depending on environmental temperature (it contains less solvent).

If white is applied on heating radiators, it may yellow depending on the temperature reached by the coated item.

In all cases for:

Indoor surfaces: Finish with 1 or 2 coats of TITANLAK Polyurethane Enamel

Outdoor surfaces: Finish with 2 or 3 coats of TITANLAK Polyurethane Enamel.

BARE SURFACES:

Wood: Sand wood following the wood grain, thoroughly clean, remove all resins or resin secretion on the surface and smooth up sharp edges. Apply TITAN Protector, Sealing-Primer or Multi-Purpose Primer depending on requirements.

Iron: TITANLUX Synthetic Rust-Preventive Primer, TITAN Electrolytic Red Lead or Multi-Purpose Primer. For outdoor surfaces, at least two coats of the selected primer will be needed. For indoor surfaces, one coat will be enough.

Other surfaces: Please consult your dealer.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Wash, lightly sand and directly apply 1 or 2 coats of TITANLAK Polyurethane Enamel.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Completely remove all previous paint coats and proceed as for bare surfaces.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2016-03

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



TITAN

011 - TITANLAK POLYURETHANE ENAMEL

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

