

# DAMP PREVENTIVE PAINT H25

Indoor. Matt



Product Code: 019



## Description

Special waterproofing indoor paint for solving humidity problems produced by capillarity, water-draining, etc. such as stains, mildew, mould growth, etc.

Breathable. It prevents liquid but not water vapour from passing through the wall, thus reducing hydrostatic pressure.

High decorative level. Fine and smooth finish. Non-yellowing. Resistant to mould growth.

Appropriate for application on building material surfaces such as cement, concrete, plaster, stone, brick, etc even if they are damp (not wet) in cellars, parking areas, bathrooms and, in general, in any poorly ventilated room.

Very low odour (no aromatic solvents).

## Technical Data

<b>Product Type</b>	Acrylic copolymer
<b>Finish</b>	Matt
<b>Colour (UNE EN ISO 11664-4)</b>	White
<b>Density (UNE EN ISO 2811-1)</b>	1.43 - 1.47 Kg/l
<b>Coverage</b>	2 - 4 m <sup>2</sup> /l
<b>Drying at 23°C 60 % RH (UNE 48301)</b>	2 hours
<b>Recoat time at 23°C 60% RH (UNE 48283)</b>	6 hours
<b>Methods of Application</b>	Brush and Roller
<b>Equipment Cleaning</b>	TITAN White Spirit or Odourless Thinner
<b>Application Temperature, RH&lt;80%</b>	+10°C - +30°C
<b>Tinting</b>	TITAN Universal Tinting Colours (max. 5%)
<b>Flash Point (UNE EN ISO 3679)</b>	45 °C
<b>Volume Solids (UNE EN ISO 3233-3)</b>	60 - 61 %
<b>VOC (UNE EN ISO 11890-2)</b>	2.004/42IIA (i) (600/500) Max. COV 450 g/l
<b>Pack sizes</b>	4 l and 750 ml

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

## Directions for use

### GENERAL REMARKS:

Carefully stir the contents in the pack. The surfaces to be painted have to be clean, dry and in good condition.

H25 Damp-Preventive Paint is suitable both for base and top coat. However, it can be repainted with any good quality water-based paint, if required.

### BARE SURFACES:

Bare surfaces: Remove dust and saltpetre with a hard-haired brush. Mould and grease, if any, have to be removed with domestic bleach thinned with water. After that, rinse thoroughly. Let to dry for 24 hours before applying the paint. Unsound surfaces, (such as cracked or loose materials, and dusty plaster) have to be patched with building material before painting.

#### MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Proceed as for bare surfaces.

#### MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Completely remove old paints in poor condition, as well as mould growth, grease and other loose particles, until reaching sound surface. Then treat as recommended for bare surfaces.

## Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

**Waste management:** Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use.

Issue date: 2018-08

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



Akzo Nobel Coatings, S.L.U – Carrer Feixa Llarga, 14-20 - Pol. Ind. Zona Franca 08040 Barcelona  
(Espanya)  
Teléfono 934 842 500  
Ins. Reg. Mer. de Barcelona T. 47631, F- 95, H. nº B-45052, Inscip. 210  
N.I.F. B-08218158

