

TITAN FOR BATHROOMS AND KITCHENS TILE ENAMEL

Indoors. Satin



Product Code: 02E

Description

Satin, easy-to-apply, synthetic enamel. To obtain high quality and soft touch finishes. Very hard and resistant to abrasion, scratches, soap and stains of liquor, juice, oil, etc. Very wash resistant. **Unsuitable for immersion or areas with condensation.**

Fields of Application

Indoor enamel to apply on ceramic tiles. **Do not use either on floor tiles or worktops.**

Technical Data

Product Type	Modified alkyd
Colour (UNE EN ISO 11664-4)	White and colour range
Density (UNE EN ISO 2811-1)	1.35 -1.65 Kg/l
Coverage (UNE 48282)	12 - 14 m ² /l
Drying at 23°C 60 % RH (UNE 48301)	4 - 5 hours
Recoat time at 23°C 60% RH (UNE 48283)	18 - 24 hours
Methods of Application	Brush and Roller
Equipment Cleaning	TITAN Synthetics and Grease Thinner, Turpentine or White Spirit
Tinting	TITAN Universal Tinting Colours or TITAN Tinting System (max. 5% in volume)
Flash Point (UNE EN ISO 3679)	40 - 41 °C
Volume Solids (UNE EN ISO 3233-3)	47,5 - 51,7%
VOC (UNE EN ISO 11890-2)	2.004/42IIA(i)(600/500) Max. COVs 300 g/l
Pack sizes	750 ml.

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Carefully clean and degrease the surface with soap and water before painting. Avoid using cleaning products made out of silicone or wax. Allow drying thoroughly.

To ensure better adhesion, joints would have to be rubbed with a brush in order to remove any dirt, moth, grease, etc.. After that, dry the surface with a clean piece of cloth.

Stir the product in the pack and apply a thin coat. If the painting surface is deeply coloured, a second coat is recommended.

Pay special attention to joints and cornes. Seal these areas with silicone to avoid damp impregnation.

5 days after painting, the surface can be washed with soft detergent. **Do not use abrasive products, scourers or brushes, because they could scratch the enamelled surface.**

If the temperature of the surface is below 10°C and if paint coat is thick, the overcoating time has to be longer. Check that the surface is suitably dry before overcoating

IMPORTANT: It reaches its final satin appearance after 3 days approx. depending on environmental temperature (it contains less solvent).

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2014-11

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



TITAN

02E - TITAN FOR BATHROOMS AND KITCHENS TILE ENAMEL

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

