

SMOOTH OXIRON SATIN

Indoors - Outdoors



Product Code: 02J

Description

Quick drying rustproof enamel-paint. Direct application on steel, no primer is needed. It provides up 10 years weathering resistance and a satin finish (6 colours) or a smooth wrought effect (3 colours). Highly decorative. Very good adhesion. Hardwearing. Resistant to impact and scratches.

The use of Smooth OXIRON allows to save time because overcoating is possible after 1 hour. In this way, most paint works can be finished in one single day.

Fields of Application

Very suitable for gratings, radiators, benches, electric appliances, doors.

Technical Data

Product Type	Alkyd styrene / Smooth wrought effect: Alkyd urethane
Finish	Satin (6 colours) and smooth wrought effect (3 colours)
Colour (UNE EN ISO 11664-4)	White and colour range
Density (UNE EN ISO 2811-1)	White: 1.28 - 1.32 Kg/l, Colours: 1.05 - 1.10 Kg/l - Smooth wrought effect: 0.95 - 0.99 Kg/l
Coverage (UNE 48282)	10 - 12 m ² /l (35 - 45 μ) / Smooth wrought effect: 12 - 14 m ² /l (30 - 35 μ)
Drying at 23°C 60 % RH (UNE 48301)	30 - 60 minutes / Smooth wrought effect: 3 - 4 hours
Recoat time at 23°C 60% RH (UNE 48283)	Minimum: 30 minutes. Maximum: 4 hours or after 5 days / Smooth wrought effect: after 18 hours
Methods of Application	Brush (just for patching) , roller and spray-gun
Equipment Cleaning	TITAN MR Thinner / Smooth wrought effect: Synthetics and Grease Thinner
Recommended Thickness (UNE EN ISO 2808)	100 μ (2 - 3 coats) / Smooth wrought effect: 60 - 100 μ
Application Temperature, RH<80%	+10°C - +30°C
Flash Point (UNE EN ISO 3679)	27° C / Smooth wrought effect: 39°C
Volume Solids (UNE EN ISO 3233-3)	46 - 50 %
VOC (UNE EN ISO 11890-2)	2.004/42IIA (i) (600/500) Max. COV 500 g/l
Pack sizes	4 l, 750 ml and 375 ml.

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Certificates

It complies with the UNE 48316:2014 Standard. Paints and varnishes. High performance corrosion resistance decorative solvent-borne coatings.

Directions for use

GENERAL REMARKS:

Smooth satin

Thoroughly stir the contents in the pack. The surfaces to be painted have to be degreased, dry and free from any poorly adhered rust particles, unsound old paint and dirt.

It is important to keep the overcoating time if a high quality finish is required. Every following coat has to be applied by the next 4 hours. If this time is exceeded, wait 5 days.

If overcoating after 4 hours, the applied surface may show creasing.

In case of application by spray-gun, the following coats can be applied after 15 - 30 minutes.

Smooth wrought effect

Thoroughly stir the contents in the pack. The surfaces to be painted have to be degreased, dry and free from any poorly adhered rust particles, unsound old paint and dirt.

Considering the peculiar characteristics of this product (metallic particles) it is recommended to apply it by roller or by spray-gun. If applied by roller, always spread the paint in the same direction in order to avoid metallized marks.

BARE SURFACES:

Smooth satin

Steel or Iron: It can be directly applied. No primer needed. If the surface shows rust, lightly sand in order to roughen the surface. Remove poorly adhered rust. In environments with medium - high corrosion, steel has to be sanded up to ST-3 of the UNE EN ISO 8501-1 standard. Under these conditions, a minimum thickness of 140 microns (3 dry coats) will be required.

Zinc, tin, galvanized: surfaces: Sand to matt and apply TITAN Multi-Purpose Primer.

Wood: TITAN Protector, TITAN Sealing Primer or TITAN Multi-Purpose Primer.

Other surfaces: Please seek advice.

Wrought smooth effect

Steel or Iron: It can be directly applied. No primer needed. If the surface shows rust, lightly sand in order to roughen the surface. Remove poorly adhered rust. In environments with medium corrosion, steel has to be sanded up to ST-3 of the UNE EN ISO 8501-1 standard. Under these conditions, a minimum thickness of 120 microns will be required. In these environments, prepare the surface with TITAN Multi-Purpose Primer. or TITANLUX Rust Preventive Primer.

Zinc, tin, galvanized: surfaces: Sand to matt and apply TITAN Multi-Purpose Primer.

Wood: Wood: TITAN Protector, TITAN Sealing Primer or TITAN Multi-Purpose Primer.

Other surfaces: Please seek advice.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Wash with soapy water, let to dry, lightly sand and directly apply Smooth OXIRON.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Thoroughly remove rust and poorly adhered previous coats by means of sandpaper or a metallic brush. For topcoats, proceed as for bare surfaces.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2018-02

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



TITAN

02J - SMOOTH OXIRON SATIN

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

