

# WATERPROOFING COATING H23

Outdoor. Semi Matt



Product Code: 03E



## Description

For roof waterproofing. Easy-to-apply. Reparation of cracked areas or where cracks are likely to appear. Suitable for surfaces to be walked on or with non-continuous traffic. Unsuitable for heavy traffic. It sticks to building materials and produces a waterproofing barrier. It contains anti mould preservative. Resistant to alkalis, such as concrete.

## Technical Data

<b>Product Type</b>	Modified acrylic
<b>Finish</b>	Semi Matt
<b>Colour (UNE EN ISO 11664-4)</b>	White and colour range
<b>Density (UNE EN ISO 2811-1)</b>	1.28 - 1.33 Kg/l
<b>Coverage</b>	0.6 - 0.7 m <sup>2</sup> /l per coat (approx. 1.5 l/m <sup>2</sup> )
<b>Drying at 23°C 60 % RH (UNE 48301)</b>	6 - 8 hours
<b>Recoat time at 23°C 60% RH (UNE 48283)</b>	18 - 24 hours Suitable to be walked on after 2 - 3 days
<b>Methods of Application</b>	Brush and Roller
<b>Thinner</b>	Water
<b>Recommended Thickness (UNE EN ISO 2808)</b>	1.0 - 1.2 mm dry film
<b>Volume Solids (UNE EN ISO 3233-3)</b>	40.5 - 41.5 %
<b>VOC (UNE EN ISO 11890-2)</b>	2.004/42IIA (c) (75/40) Max. VOC 5 g/l.
<b>Pack sizes</b>	15 l, 4 l and 1 l

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

## Certificates

Determination of tensile strength and elongation at break UNE-EN ISO1798: 2001: Tensile strength:  $\sigma$ : 0.98MPa / Elongation at break  $\epsilon$ : 665%

## Directions for use

### GENERAL REMARKS:

Carefully stir the contents in the pack.

The surfaces to be painted have to be clean, dry and in good condition.

ATTENTION VERY IMPORTANT.

DO NOT APPLY:

At temperatures below 7 ° C.

With relative humidity equivalent to or above 80%

If rain is foreseen in the next hours.

Failure to follow these instructions may lead to unsatisfactory results in the application. Industrias TITAN will not accept any claim if these directions have not been taken into account.

If there are more than 1 mm wide cracks, it is advisable to repair them and/or to reinforce them with a strip of waterproofing elastic material, between the applied coats of H23 Waterproofing Coating.

To thoroughly waterproof horizontal enclosed surfaces, the application of H23 Waterproofing Coating has to be extended until the adjoining vertical walls up to a certain height, and the angles between horizontal and vertical surfaces have to be reinforced, if necessary.

In order to improve the resistance against breakage of the applied film, a reinforcing layer of continuous fibre can be added between the applied coats of H23 Waterproofing Coating. This addition is especially convenient on areas to be walked on more often.

While the paint is not thoroughly dry, it may be damaged by water.

#### **BARE SURFACES:**

Clean and remove all unsound residue. Smooth and level out the slopes or unevenness of the surface to be painted, in order to avoid possible floods. Thin the first coat with 25% water. It is important to obtain a 1-1.2 mm. thick dry film to achieve an elasticity which allows a continuous film without breaks, where cracks appear on the treated area

#### **MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:**

Directly apply the paint with prior sanding or brushing. Thin the first coat with 25% water. Apply a second unthinned coat.

#### **MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:**

Thoroughly remove old coats and proceed as for bare surfaces.

## Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

**Waste management:** Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use.

It contains BCM, IPU, IPC, Terbutryn to protect the initial properties of the treated article.

Issue date: 2018-09

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



Akzo Nobel Coatings, S.L.U – Carrer Feixa Llarga, 14-20 - Pol. Ind. Zona Franca 08040 Barcelona (España)  
Teléfono 934 842 500  
Ins. Reg. Mer. de Barcelona T. 47631, F- 95, H. nº B-45052, Inscrp. 210  
N.I.F. B-08218158

