

TITAN VARNISH FOR WOODEN FLOORS

Indoors. Satin



Product Code: 044

Description

One-component polyurethane varnish. Reinforced formula. Easy application. Long lasting, great hardness and resistance to rubbing, alcohol and detergents. Wash resistant. Unalterable by contact with oil, wine, fruit juice, etc. Low odour.

Fields of Application

Special for embellishment and maintenance of wooden floors and stairs.

Technical Data

Finish	Satin
Colour (UNE EN ISO 11664-4)	Clear
Density (UNE EN ISO 2811-1)	0.91 - 0.93 Kg/l
Coverage (UNE 48282)	12 - 16 m ² /l
Drying at 23°C 60 % RH (UNE 48301)	3 - 4 hours
Recoat time at 23°C 60% RH (UNE 48283)	18 - 24 hours
Methods of Application	Brush,
Equipment Cleaning	TITAN Odourless Thinner or White Spirit
Application Temperature, RH<80%	+10°C - +30°C
Flash Point (UNE EN ISO 3679)	41° C.
Volume Solids (UNE EN ISO 3233-3)	42 - 43 %
VOC (UNE EN ISO 11890-2)	2.004/42IIA(i)(600/500)Máx. COV[s] 450g/l.
Pack sizes	4 l, 1 l, 750 ml and 500 ml

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Thoroughly stir the contents in the can. The wood moisture content must not exceed 12% in hard wood and 15% in soft wood. Very absorbent woods may require three coats. **Wait 24 hours before stepping on the surface.**

Tropical or resinous wood: Please refer to the Technical Service.

BARE SURFACES:

Clean with solvent eventual spots of oil, paint or wax, and lightly sand wood. Dust off and apply one coat of TITAN Polyurethane Varnish for Wooden Floors following wood grain. This first coat has to be glossy. 24 hours later gently sand, remove dust and apply a second coat of TITAN Varnish for Wooden Floors. This second coat can be glossy or satin depending on the required finish. Upon staining wood with water-based walnut stain, allow drying for 10 hours minimum before applying the first thin varnish coat.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Ensure maximum adhesion by sanding, mechanically if possible; wash with warm water and powdered detergent and rinse out. Once dry (24 - 48 hours) clean joints and cracks with solvent to remove any trace of wax and polishing, and proceed as described for bare wood.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Unsound varnish (cracked or flaky) or two-component varnishes have to be completely removed by deeply scrapping and proceed as for bare wood.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2014-05

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



TITAN

044 - TITAN VARNISH FOR WOODEN FLOORS

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

