

# TITAN MR THINNER



**Product Code:** 059

## Description

Mixture of ethyl and meta xylenes. Medium evaporation thinner. High thinning power.

## Fields of Application

For thinning quick drying (Hammered and Smooth Oxiron), epoxy, polyurethane and chlorinated-rubber paints.

## Technical Data

<b>Colour (UNE EN ISO 11664-4)</b>	Colourless
<b>Density (UNE EN ISO 2811-1)</b>	0.85 - 0.88 Kg/l
<b>Flash Point (UNE EN ISO 3679)</b>	25 °C
<b>Pack sizes</b>	1 l and 250 ml.

## Directions for use

### GENERAL REMARKS:

It quickly thins paints. Therefore, a careful use is required. In Epoxy or Polyurethane paints, it acts as a thinner. For this reason, previous compatibility tests are recommended.

This thinner is highly suitable for applying enamels by spray-gun. In this case, the recommended mixing rate would be 15 - 20%. For brush or roller, the mixing rate would be 5 - 10%.

This thinner can be used for alkyd paints, but in small amounts, since it can damage previous unsuitably dry coats.

## Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

**Waste management:** Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use.

Issue date: 2019-11

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



Akzo Nobel Coatings, S.L.U – Carrer Feixa Llarga, 14-20 - Pol. Ind. Zona Franca 08040 Barcelona (Espanya)  
Teléfono 934 842 500  
Ins. Reg. Mer. de Barcelona T. 47631, F- 95, H. nº B-45052, Inscip. 210  
N.I.F. B-08218158

