

OUTDRIVE ANTIFOULING



Product Code: 07C

Description

ANTIFOULING tin-free paint. It avoids marine growth on the surfaces of outboard motors, propellers, flaps, rudders, etc. This special formula, based on HOSTAFLON ®, improves the performance of the engine by reducing water-friction.

Fields of Application

Outboard motors, propellers, flaps, rudders, etc.

Technical Data

Product Type	Vinyl
Finish	Matt
Colour (UNE EN ISO 11664-4)	Black and grey
Density (UNE EN ISO 2811-1)	1.60 - 1.70 Kg/l
Drying at 23°C 60 % RH (UNE 48301)	25 - 30 minutes
Recoat time at 23°C 60% RH (UNE 48283)	Once dry.
Methods of Application	Spray
Equipment Cleaning	TITAN YATE Thinner
Recommended Thickness (UNE EN ISO 2808)	50 - 100 µ dry film (2 - 3 coats applied)
Application Temperature, RH<80%	+10°C - +30°C
Pack sizes	500 ml.

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Strongly shake the spray can before use. The surface has to be sanded, clean, dry and salt-free (wash it). Do not paint if the surface is under direct sunlight or if it has dew on it.

For patching up bare metal surfaces in quick-drying painting operations, it is possible to apply 2 coats of TITAN YATE Spray Marine Primer before applying the Outdrive Antifouling.

BARE SURFACES:

Degrease, lightly sand and dust-off. Spray two full coats of Outdrive Antifouling, at a spraying distance of approximately 15 - 25 cm.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

If they are free from fouling, lightly sand and dust off. Spray two full coats of Outdrive Antifouling, at a spraying distance of approximately 15 - 25 cm.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

If they have bare metal areas or with rests of primers and/or previous antifouling coats, thoroughly remove them until reaching a clean, sound metal surface. Apply 2 coats of TITAN YATE Epoxy Primer and proceed as for previously coated outdrive elements in good condition.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2018-08

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



TITAN

07C - OUTDRIVE ANTIFOULING

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

