

SELF-POLISHING UNIVERSAL ANTIFOULING. MEDIUM SPEED.

MEDIUM SPEED - SAILING BOATS AND MOTORBOATS

TITAN



Product Code: 07M

Description

Antifouling containing HOSTAFロン®. Self-polishing by controlled solubility. Biologically active for the whole product life. It can be directly applied on the majority of well-adhered anti-fouling coats. It does not accumulate old coatings. Recommended for any kind of sailing boats and motorboats of medium speed (up to 20 knots).

Fields of Application

Self-polishing antifouling for submerged surfaces of Polyester, Wood, Steel and Aluminium. Recommended for sailing boats and motorboats of medium speed.

Technical Data

Finish	Silky semi-matt
Colour (UNE EN ISO 11664-4)	White, colour range and permanent white
Density (UNE EN ISO 2811-1)	White: 1.6 - 1.7 Kg/l / Colours: 1.7 - 2.2 Kg/l
Coverage (UNE 48282)	10 - 12 m ² /l per coat.
Drying at 23°C 60 % RH (UNE 48301)	1 hour / Immersion (Launching): after 12 hours and up to 6 months
Recoat time at 23°C 60% RH (UNE 48283)	6 hours
Methods of Application	Brush, roller and spray-gun.
Thinner	TITAN YATE Thinner
Recommended Thickness (UNE EN ISO 2808)	80 - 90 dry μ in two coats.
Application Temperature, RH<80%	+10°C - +30°C
Flash Point (UNE EN ISO 3679)	25 °C
Volume Solids (UNE EN ISO 3233-3)	60 - 66 %
Pack sizes	2.5 l and 750 ml

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

On TITAN YATE Epoxy Primer, apply the antifouling between 12-24 hours after the last coat.

Important: In areas of higher wear, such as waterline, keel, rudder, etc., it is recommended an additional coat, since water turbulence speeds up self-polishing.

BARE SURFACES:

Polyester: De-grease with TITAN YATE Thinner and apply 1-2 coats of TITAN YATE Epoxy Primer in intervals of 24 hours (For

osmosis prevention, apply m-150 Epoxy Primer).

Metal: Apply 3-4 coats of TITAN YATE M-150 Epoxy Primer, strictly following the instructions of the pack.

Wood: It has to be clean and dry. Apply 2 coats of TITAN YATE Epoxy Primer, the 1st coat thinned with 20% TITAN YATE Thinner.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

On the majority of old well-adhered antifouling coats wash with fresh water jet and apply directly.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

On poorly adhered coats, remove completely with TITAN Paint Stripper, followed by a wash with fresh water and afterwards treat it as a bare surface.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

Waste management: Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use.

Issue date: 2016-01

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



TITAN

INDUSTRIAS TITAN S.A.U.
España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94
Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764



07M - SELF-POLISHING UNIVERSAL ANTIFOULING. MEDIUM SPEED.