

TITAN YATE POLYURETHANE VARNISH

Gloss

TITAN



Product Code: 07Z

Description

High quality varnish which is based on polyurethane resin and contains ultraviolet filters. It is bright, hard and has an extraordinary resistance under rough weather conditions. Because of its quick drying and easy application, it is an ideal varnish for DIY and for professional use.

Fields of Application

Because of its excellent flexibility, it can be applied on soft and hard woods, both indoors and outdoors. For varnishing wood in yachts and fishing boats, and for other structures in coastal areas or in very wet environments.

Technical Data

Product Type	Urethaned alkyd
Finish	Gloss
Colour (UNE EN ISO 11664-4)	Clear
Density (UNE EN ISO 2811-1)	0.93 - 0.95 Kg/l
Coverage (UNE 48282)	14 - 18 m ² /l
Drying at 23°C 60 % RH (UNE 48301)	3 - 4 hours
Recoat time at 23°C 60% RH (UNE 48283)	24 hours
Methods of Application	Air Spray-gun, Roller, Brush
Thinning	Air Spray-gun: 20 - 30%. Brush and Roller: 3 - 5%
Thinner	TITAN Synthetics and Grease Thinner or White Spirit
Equipment Cleaning	TITAN Synthetics and Grease Thinner, or White Spirit
Recommended Thickness (UNE EN ISO 2808)	75 - 100 µ dry film
Flash Point (UNE EN ISO 3679)	44 °C
Volume Solids (UNE EN ISO 3233-3)	50 - 52 %
Pack sizes	750 ml

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

The surface has to be sanded, clean, dry and free from salt (wash it). Do not varnish either with direct sunlight or with dew.

Hard wood, teak, iroko, or tropical wood: Thoroughly wash the surface with TITAN YATE Thinner (to remove resin). Thin the first coat with 10% TITAN Synthetics and Grease Thinner or White Spirit. Wait 24 hours to see if there is any resin exudation or delay in the varnish drying. If this is the case, wash again with TITAN YATE Thinner. Sand between coats. Finish with 2 - 3

unthinned coats of TITAN YATE Polyurethane Varnish.

BARE SURFACES:

Thin the first coat with 20 - 30% TITAN Synthetics and Grease Thinner. or White Spirit. Sand between coats. Apply 2 - 3 coats of TITAN YATE Polyurethane Varnish.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Sand to matt old but well adhered varnish and apply 2 - 3 unthinned coats of TITAN YATE Polyurethane Varnish.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Thoroughly remove old varnish in poor condition by sanding, brushing or with TITAN Plus Paint-Stripper until obtaining a wooden surface in good condition. After that, proceed as for non-prepared surfaces.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

Waste management: Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use.

Issue date: 2018-08

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



TITAN

07Z - TITAN YATE POLYURETHANE VARNISH

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

