

SATIN PICTURE VARNISH



Product Code: 091 0020



Description

Satin finish reversible protective varnish. Non-yellowing. Lightfast. It dries by evaporation. Permanent paleness. It protects pictures against grease, dust and air pollution. Elastic, non-cracking. Long-lasting, non-ageing.

Fields of Application

To be used for varnishing pictures painted with oil or acrylic colours.

Technical Data

Product Type	Acrylic resin dissolved in white spirit and turpentine.
Finish	Opal. Satin
Density (UNE EN ISO 2811-1)	0.80 - 0.90 Kg/l
Drying at 23°C 60 % RH (UNE 48301)	1 - 1:30 hours
Methods of Application	Brush or flat brush
Thinner	Turpentine oil or petroleum spirit (white spirit)
Equipment Cleaning	Brush Cleaner
Flash Point (UNE EN ISO 3679)	40 °C
Volume Solids (UNE EN ISO 3233-3)	24 - 26 %
Pack sizes	1 l, 250 ml and 100 ml.

Directions for use

GENERAL REMARKS:

Previously shake the product in the bottle.

Directly apply by thin coats on thoroughly dry colours.

Do not mix it either with oil or with oil colours; not to be used as a medium.

This varnish is reversible. If required, it can be completely removed by rubbing the surface with a soft cloth moistened with petroleum spirit (white spirit) or turpentine oil, and well drained.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2015-03

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.

TITAN

091 0020 - SATIN PICTURE VARNISH

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

