

# MINERAL PITCH



**Product Code:** 091 0040

## Description

Required for artistic and handicraft tasks. This is the classical mineral pitch used for patinas, imitation of ageing or highlighting engraved metals, making frames and moulds more attractive and decorating objects.

## Fields of Application

Used in professional, artistic and handicraft tasks. Ideal for the application on wood, canvas, paper, cardboard, gypsum, plaster, brick, cement, stone, clay, steel and other metals.

## Technical Data

<b>Finish</b>	Dark brown liquid. Gloss
<b>Density (UNE EN ISO 2811-1)</b>	0.83 - 0.87 Kg/l
<b>Drying at 23°C 60 % RH (UNE 48301)</b>	1.15 - 1.45 h
<b>Methods of Application</b>	Paintbrush, brush, sponge, by hand, air brush or by immersion.
<b>Thinning</b>	Turpentine Oil or Petroleum Spirit.
<b>Equipment Cleaning</b>	Brush Cleaner.
<b>Flash Point (UNE EN ISO 3679)</b>	> 41 °C
<b>Pack sizes</b>	1 l, 250 ml and 100 ml

## Directions for use

### GENERAL REMARKS:

Carefully shake the contents in the bottle. To be applied by very thin layers, directly on the above-mentioned kinds of surfaces or on dry paint (except for varnishes based on white spirit). If applied by too thick coats it can easily become brittle because of its extraordinary hardness.

## Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2015-03

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



**TITAN**

091 0040 - MINERAL PITCH

**INDUSTRIAS TITAN S.A.U.**  
España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94  
Portugal: Rua Fonte Cova, 51 - 4475-031 Maia  
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia  
T. +351 229 865 450 - F. +351 229 810 764

