

ACUALUX TITAN

Indoors - Outdoors. Satin and Metallized Satin



Product Code: 092

Description

High quality, high coverage permanent paint. To be directly used on wood, cardboard, plaster and other porous surfaces. Intermixable colours.

Fields of Application

Indoor and outdoor paint. To be applied on wood, canvas, paper, concrete, stone, bisque, clay, plaster, etc.

Technical Data

| | |
|---|---|
| Finish | Satin and Metallized Satin |
| Colour (UNE EN ISO 11664-4) | White and colour range |
| Density (UNE EN ISO 2811-1) | White: 1.35 - 1.39 Kg/l , Colours: 1.20 - 1.40 Kg/l, Metallized: 1.05 - 1.30 Kg/l |
| Coverage (UNE 48282) | 12 - 16 m ² /l |
| Drying at 23°C 60 % RH (UNE 48301) | 30 - 60 minutes |
| Recoat time at 23°C 60% RH (UNE 48283) | 6 - 8 hours |
| Methods of Application | Brush, roller and spray-gun. |
| Thinning | Water |
| Equipment Cleaning | Water |
| Application Temperature, RH<80% | +10°C - +30°C |
| Tinting | TITAN Universal Tinting Colours or Water Based Professional Dye |
| Volume Solids (UNE EN ISO 3233-3) | White: 40 - 41% / Colours: 40 - 43% |
| Pack sizes | 100 ml, 250 ml and 500 ml (depending on colour), Metallized: 50 ml, 100 ml, 250 ml and 500 ml |

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Carefully stir the contents in the pot. The surfaces to be painted have to be clean, dry and sound.

Stains on fabric, wash before 5 minutes with water and detergent.

ATTENTION VERY IMPORTANT.

DO NOT APPLY:

At temperatures below 7° C.

With relative humidity equalivent to or above 80%

If rain is foreseen in the next hours.

Failure to follow these instructions may lead to unsatisfactory results in the application, such as patches of different colour or irregular thin lines on areas of the paint film (similar to snail trails, etc..). Industrias TITAN will not accept any claim if these

directions have not been taken into account. Please pay special attention to dark colours, as some of them are more susceptible to the occurrence of the phenomena mentioned above. This is an additional reason to observe the instructions and precautions listed.

BARE SURFACES:

Bare canvas: Apply one or two coats of TITAN Gesso Universal Primer.

Plaster or wood: Apply a full coat of TITAN Sealing Primer or Acualux Gloss Varnish. The right thinning rate for the varnish is 1 part of varnish and 3 parts of water. Finish with one or two coats of Acualux TITAN.

Other surfaces : Seek advice.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Wash, softly sand and directly apply Acualux TITAN.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

If they are in poor condition, thoroughly remove them and proceed as on non prepared surfaces.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Before applying the product on a large surface where scaffolding must be employed to lift more than two floor levels, it is essential to request the visit of a technician of the TITAN After-Sales Service, who will ensure that all details in our technical sheet are known, check the surface state, and provide on-site advice on environmental and atmospheric conditions in order to guarantee a perfect finish.

If these directions are not observed, Industrias TITAN, S.A. will not be held responsible for the success of the application.

Protect the packs from temperatures below 0°C

Issue date: 2015-06

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



TITAN

092 - ACUALUX TITAN

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

