

WATERBASED INTUMESCENT PAINT A80

Indoors. Matt



Product Code: 102

Description

Single coat intumescent paint for protecting steel structures against fire, both for open profiles (I-shaped and H-shaped). It swells as a result of heat exposure and develops an isolating foam which protects the structural steel and delays the heat propagation. It provides stability against fire in metallic structures ranging from R90 in open profiles to R30 in hollow profiles. Quick-drying and short overcoating interval. No repainting limit.

Fields of Application

Indoor application. It is also possible to apply this paint on outdoor surfaces partially exposed to weathering provided it is overcoated with an appropriate paint or enamel. Suitable for steel previously prepared with a compatible primer. To be used in workshops, new works and maintenance works in rural, urban and industrial environments.

Technical Data

Finish	Matt
Colour (UNE EN ISO 11664-4)	White.
Density (UNE EN ISO 2811-1)	1.29 - 1.31 Kg/l
Coverage (UNE 48282)	2 Kg/m ² for 1000 dry μ
Drying at 23°C 60 % RH (UNE 48301)	8 hours
Recoat time at 23°C 60% RH (UNE 48283)	8 hours
Methods of Application	Airless. Brush (3 coats are required to achieve the recommended thickness)
Thinning	Airless: 0 - 5% / Brush: 0 - 5%
Nozzle Diameter	Airless: 0.025" - 0.030"
Nozzle Pressure	Airless: 180 - 250 bar
Thinner	Water
Equipment Cleaning	Water
Recommended Thickness (UNE EN ISO 2808)	Dry: 750 microns / Wet: 1100 microns (maximum per coat)
Application Temperature, RH<80%	+5°C - +35°C
Volume Solids (UNE EN ISO 3233-3)	60 - 70%
VOC (UNE EN ISO 11890-2)	2.004/42IIA (i) (140/140) Max. COV 30 g/l
Pack sizes	25 Kg

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Certificates

Fire resistance of building structures: UNE-ENV Standard 13381-8.

Directions for use

GENERAL REMARKS:

The surfaces to be painted have to be free from dust, grease and oil, dry and in good condition. Before use, homogenise the product with a mechanical shaker. Make sure there are no pigment rests at the bottom of the pot.

If necessary, adjust viscosity with water. Before every use, clean the sprayer with water. A80 Intumescent Paint has to be applied on a base coat of compatible anticorrosive primer.

Always paint at a temperature which has to be 3°C above dew point. In contact with excess moisture, the intumescent paint gets damaged.

Steel: It is advisable to sandblast the surface up to Sa 2 ½ grade of the ISO 8501-1 standard or by means of manual or mechanical cleaning, up to ST-3 grade of this same standard. Apply the required primer and finish with the A80 Waterbased Intumescent Paint. Pay attention to the thickness in microns prescribed by the Project Management, considering the profile characteristics and the required performance.

If the surfaces are previously primed, they must have a normal appearance and be dry and free from pollutants. It is advisable to previously test compatibility. If the surface has been coated with zinc primers (epoxy with high zinc content or zinc based silicates), it will have to be clean, dry and free from zinc salts. Any damage on the surface will have to be repaired before applying the A80 Waterbased Intumescent Paint.

The total thickness of the dry primer base coat must never exceed 150 microns.

The most suitable system for applying A80 Waterbased Intumescent Paint is by airless spraying. The thickness to be achieved is 750 dry µ per coat, by means of repeated crossed spraying (it is advisable to remove filters). Brush is also acceptable for small surfaces, even though the final appearance will show brush marks. Application by roller is not recommended.

The final film thickness of the intumescent paint will be determined by the massivity and the fire resistance of the profile to be painted. It will be assessed in accordance with the A80 Waterbased Intumescent Paint certificate.

All paints and enamels of our Professional / Industrial ranges (except chlorinated rubber) can be applied on the A80 Waterbased Intumescent Paint, provided that the thickness is not excessive (<90µ) as this can affect the performance of fire protection because it may limit the swelling of the intumescent paint.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2016-09

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



TITAN

102 - WATERBASED INTUMESCENT PAINT A80

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

