

# DECK WATERPROOFING FIBERED COATING A8

Outdoor. Semi Matt



Product Code: 12F

## Description

For roof waterproofing. Easy-to-apply. Repairation of cracked areas or where cracks are likely to appear. Suitable for surfaces to be walked on or with non-continuous traffic. Unsuitable for heavy traffic. It sticks to building materials and produces a waterproofing barrier. It contains anti-mould and anti-algae preservative. Resistant to alkalis, such as concrete.

## Technical Data

<b>Product Type</b>	Modified acrylic
<b>Finish</b>	Semi matt
<b>Colour (UNE EN ISO 11664-4)</b>	White and colour range
<b>Density (UNE EN ISO 2811-1)</b>	1.27 - 1.33 Kg/l.
<b>Coverage (UNE 48282)</b>	0.6 - 0.7 m <sup>2</sup> /l (approx. 1.5 l/m <sup>2</sup> )
<b>Drying at 23°C 60 % RH (UNE 48301)</b>	6 - 8 hours
<b>Recoat time at 23°C 60% RH (UNE 48283)</b>	18 - 24 hours. Walkable: 2 - 3 days
<b>Methods of Application</b>	Brush and roller
<b>Thinner</b>	Water
<b>Recommended Thickness (UNE EN ISO 2808)</b>	1.0 - 1.2 mm. dry film
<b>Volume Solids (UNE EN ISO 3233-3)</b>	40.5 - 41.5 %
<b>VOC (UNE EN ISO 11890-2)</b>	2.004/42IIA (c) (75/40) Max. COV 5 g/l.
<b>Pack sizes</b>	15 l, 4 l and 1 l

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

## Directions for use

### GENERAL REMARKS:

Carefully stir the contents in the pack. The surfaces to be painted have to be clean, dry and in good condition.

ATTENTION, VERY IMPORTANT. DO NOT APPLY:

At temperatures below 7°C

If rain is foreseen in the next hours following application.

Otherwise, the application result may not be satisfactory. Industrias TITAN, S.A. will not accept any claimed if these instructions are not observed.

If there are more than 1 mm wide cracks, it is advisable to repair them and/or to reinforce them with a strip of waterproofing elastic material, between the applied coats of A8 Deck Waterproofing Fibered Coating.

To thoroughly waterproof horizontal enclosed surfaces, the application of A8 Deck Waterproofing Fibered Coating has to be extended until the adjoining vertical walls up to a certain height, and the angles between horizontal and vertical surfaces have to be reinforced, if necessary.

In order to improve the resistance against breakage of the applied film, a reinforcing layer of continuous fibre can be added between the applied coats of A8 Deck Waterproofing Fibered Coating. This addition is especially convenient on areas to be walked on more. While the paint is not thoroughly dry, it may be damaged by water.

#### **BARE SURFACES:**

Clean and remove all unsound residue. Smooth and level out the slopes or unevenness of the surface to be painted, in order to avoid possible floods. Thin the first coat with 25% water. It is important to obtain a 1-1.2 mm. thick dry film to achieve an elasticity which allows a continuous film without breaks, where cracks appear on the treated area

#### **MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:**

Directly apply the paint after having washed or brushed the surface. Thin the first coat with 25% water. Apply a second coat of pure product.

#### **MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:**

Thoroughly remove old paint coats and proceed as for non-prepared surfaces.

## Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Protect the packs from temperatures below 0°C

Issue date: 2018-11

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



# TITAN

12F - DECK WATERPROOFING FIBERED COATING A8

#### **INDUSTRIAS TITAN S.A.U.**

**España:** P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

**Portugal:** Rua Fonte Cova, 51 - 4475-031 Maia  
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia  
T. +351 229 865 450 - F. +351 229 810 764

