

SYNTHETIC VARNISH D7

Indoo . Satin



Product Code: 131

Description

High solid polyurethane Varnish. Special for protection and high decoration of fine wood finishing. Lacquered appearance. Smooth and silky. Easy application. Quick-drying. High resistance to scratching, stains and washes. Very low odour. It can be applied on: doors, cupboards, tables, chairs, panelling, stair railing, etc.

Technical Data

Product Type	Urethaned alkyd with high solid content
Finish	Satin
Colour (UNE EN ISO 11664-4)	Clear
Density (UNE EN ISO 2811-1)	0.92 - 0.96 Kg/l
Coverage (UNE 48282)	11 - 15 m ² /l
Drying at 23°C 60 % RH (UNE 48301)	3 - 5 hours
Recoat time at 23°C 60% RH (UNE 48283)	18 - 24 hours
Methods of Application	Brush, roller and spray-gun
Equipment Cleaning	White Spirit.
Application Temperature, RH<80%	+10°C - +30°C
Flash Point (UNE EN ISO 3679)	41 °C
Volume Solids (UNE EN ISO 3233-3)	50 - 51 %
VOC (UNE EN ISO 11890-2)	2.004/42IIA (e) (500/400) Max. COV 400 g/l
Pack sizes	4 l

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Thoroughly stir the contents in the pack. The surfaces have to be clean, dry and suitably prepared. The wood moisture content must not exceed 12% in hard wood and 15% in soft wood. Tropical or resinous wood: Please refer to the Technical Service.

BARE SURFACES:

Remove with solvent the existing stains or oil, paint or wax. Lightly sand, dust off and apply a thin coat. After 24 hours, lightly sand, dust off and apply a second coat.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Wash, lightly sand and directly varnish.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Thoroughly remove unsound previous varnish coats and proceed as for bare wood.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2018-09

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.

TITAN

131 - SYNTHETIC VARNISH D7

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

