

WATER BASED SILOXANE FIXATIVE A16

Indoor - Outdoor



Product Code: 149

Description

Recommended fixative for A13 Silicone Based Façade Paint, in order to produce a breathable system containing silicone, which allows the passage of water vapour but stops rainwater.

Fixative with high impregnation power. For sealing very porous surfaces, plaster, etc.

It improves the paint adhesion on the surface. Moreover it avoids unevenness in the final finish because of irregular absorption areas.

Technical Data

Product Type	Siliconed Acrylic.
Colour (UNE EN ISO 11664-4)	Colourless when applied. Bluish in the pack.
Density (UNE EN ISO 2811-1)	0.90 - 1.10 Kg/l
Coverage (UNE 48282)	2 - 5 m ² /l
Drying at 23°C 60 % RH (UNE 48301)	20 - 30 minutes
Recoat time at 23°C 60% RH (UNE 48283)	4 - 6 hours
Methods of Application	Brush, roller and spray-gun
Thinner	Water
Application Temperature, RH<80%	+10°C - +30°C. Do not apply if rain is foreseen in the following hours.
Volume Solids (UNE EN ISO 3233-3)	12.5 - 13.5 %
VOC (UNE EN ISO 11890-2)	2004/42/IIA (h) (50/30) Max. COV 5 g/l
Pack sizes	10 l and 4 l

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Carefully stir in the contents in the pack. The surfaces to be painted have to be clean, dry and in good condition.

BARE SURFACES:

If the surfaces are in poor condition, repair all the damaged areas. Remove all poorly adhered or inconsistent material. Remove dirt and existing dust. On very porous surfaces, apply a first coat, 20 - 30% thinned with water. Before it gets dry, apply a second coat of unthinned product.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Protect the packs from temperatures below 0°C

Issue date: 2018-07

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.

TITAN

149 - WATER BASED SILOXANE FIXATIVE A16

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

