

POLYURETHANE SATIN ENAMEL D4

Indoor - Outdoor. Satin



Product Code: 150

Description

Quick-drying. Premium quality, fine, soft-feel satin finishes with an excellent lacquered look. Great resistance to wearing, scratching, soaps, liqueur, juice and oil stains. Highly wash-resistant. Snow white. Non-yellowing. Low odour.

Fields of Application

Especially suitable for lacquering wooden or metal furniture, doors, windows, etc, and all surface where a lacquered finish is required.

Technical Data

Product Type	Alkyd urethaned
Finish	Satin
Colour (UNE EN ISO 11664-4)	White
Density (UNE EN ISO 2811-1)	1.16 - 1.18 Kg/l
Coverage (UNE 48282)	12 - 14 m ² /l
Drying at 23°C 60 % RH (UNE 48301)	4 - 5 hours
Recoat time at 23°C 60% RH (UNE 48283)	18 - 24 hours
Methods of Application	Brush, roller
Equipment Cleaning	Synthetics and Grease Thinner or White Spirit
Application Temperature, RH<80%	+10°C - +30°C
Flash Point (UNE EN ISO 3679)	40° C
Volume Solids (UNE EN ISO 3233-3)	50 - 52 %
VOC (UNE EN ISO 11890-2)	2.004/42IIA (d) (400/300) Max. COV 300 g/l.
Pack sizes	10 l and 4 l

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Thoroughly stir the contents in the pack. The surfaces have to be clean, dry and suitably prepared.

Remove all existing rests of dirt, grease, poorly adhered rust and previous coatings by using thinner or paint stripper, depending on requirements.

BARE SURFACES:

Wood: Sand wood following the wood grain, thoroughly clean, remove all resins or resin secretion on the surface and smooth up sharp edges. Apply D12 Sealing-Primer or A18 Water-based Sealing Primer depending on requirements.

Iron: TITANLUX Synthetic Rust-Preventive Primer or Multi-Purpose Primer. For outdoor surfaces, at least two coats of the selected primer will be needed. For indoor surfaces, one coat will be enough.

Other surfaces: Please seek advice.

In all cases for:

Indoor surfaces: Finish with 1 or 2 coats of D4 Satin Polyurethane Enamel.

Outdoor surfaces: Finish with 2 or 3 coats of D4 Satin Polyurethane Enamel.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Wash, lightly sand and directly apply.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Completely remove all previous paint coats and proceed as for bare surfaces.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2014-01

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.

TITAN

150 - POLYURETHANE SATIN ENAMEL D4

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

