

PORE SEALER NITRO LACQUER

Indoor. Satin



Product Code: 15H

Description

Nitrocellulose lacquer, gloss finish, with a wide field of application. Good gloss retention and transparency. Easy application. Quick-drying. Easy repainting.

Fields of Application

As a finishing lacquer for items made of solid wood, veneer and plywood.

Technical Data

Finish	Satin (Gloss at 60°: 65±5)
Colour (UNE EN ISO 11664-4)	Clear
Density (UNE EN ISO 2811-1)	0.91 - 0.93 Kg/l
Coverage (UNE 48282)	As a finish lacquer: 7 - 11 m ² /l, as a base coat: 3 - 4 m ² /l
Drying at 23°C 60 % RH (UNE 48301)	45 minutes
Recoat time at 23°C 60% RH (UNE 48283)	Minimum: 5 hour. Maximum: Indefinite with previous sanding
Methods of Application	Brush, Roller and Air Spray-gun
Thinning	Brush and Roller: 20%, Air spray-gun: 30%
Nozzle Diameter	Air spray-gun: 1.7 mm
Nozzle Pressure	Air spray-gun: 3 atm
Thinner	Brush and Roller: 15 L Brush Nitro Lacquer Thinner, Air spray-gun: 15 M Spray-gun Nitro Lacquer Thinner
Equipment Cleaning	Nitro Lacquer Thinner
Recommended Thickness (UNE EN ISO 2808)	Base coat: 300 - 320 ml/m ²
Application Temperature, RH<80%	+10°C - +30°C
Flash Point (UNE EN ISO 3679)	15 °C
Volume Solids (UNE EN ISO 3233-3)	18 - 22 %
Pack sizes	4 l, 750 ml and 375 ml

Directions for use

GENERAL REMARKS:

Stir the product in the pack before use.

Avoid repeated hand strokes. Quick-drying product. Preferably apply it by spray-gun.

BARE SURFACES:

The surface to be varnished will have to be previously primed with TITAN Nitro Lacquer Pore Sealer.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Before repainting, sand one part of the surface and apply on it TITAN Finish Nitro Lacquer. Test the result on the old varnish. If any unexpected result appears, thoroughly remove the old varnish and proceed as for non-prepared surfaces.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Thoroughly remove old coats and proceed as for bare surfaces.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2014-05

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.

**TITAN**

15H - PORE SEALER NITRO LACQUER

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

