

SR RUST PREVENTIVE PRIMER 806



Product Code: 806

Description

Quick drying alkyd primer. It obtains its rust prevent effect by incorporating active non toxic pigments. Easy overcoating. To be used as a workshop primer because of its resistance to rust.

Fields of Application

Suitable as general use anticorrosive primer in environments with moderate chemical aggression. For iron and steel, both indoors and outdoors and where especially short overcoating intervals are required.

Technical Data

| | |
|--|---|
| Product Type | Modified alkyd |
| Finish | Matt |
| Colour (UNE EN ISO 11664-4) | RAL Grey 7035 |
| Density (UNE EN ISO 2811-1) | 1.31 - 1.38 Kg/l |
| Coverage (UNE 48282) | 10 - 12 m ² /l (25 - 30 dry microns) |
| Drying at 23°C 60 % RH (UNE 48301) | 20 - 40 minutes |
| Recoat time at 23°C 60% RH (UNE 48283) | Minimum: 10 hours. Maximum: None |
| Methods of Application | Brush (Just for patching), Air Spray-Gun and Airless (The data quoted are only hints) |
| Thinning | Brush, Roller: 0-5% , Air Spray-Gun: 10-15%, Airless: 0-5%, |
| Nozzle Diameter | Air Spray-Gun: 1.5 mm., Airless: 0.018"-0.021" |
| Nozzle Pressure | Air Spray-Gun: 3-4 bar, Airless: 175 bar |
| Thinner | 872 or 874 Thinner (depending on room temperature) |
| Equipment Cleaning | 872 or 874 Thinner (depending on room temperature) |
| Recommended Thickness (UNE EN ISO 2808) | 25 - 30 dry microns |
| Flash Point (UNE EN ISO 3679) | 27 °C |
| Volume Solids (UNE EN ISO 3233-3) | 47 - 49 % |
| Pack sizes | 10 l, 4 l and 1 l. |

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Carefully stir the product in the pack.

The surfaces to be painted have to be clean, dry and sound.

BARE SURFACES:

Iron: Remove rust by sandblasting up to Sa 2 ½ grade of the ISO 8501-1 standard or by means of manual or mechanical cleaning, up to ST3 grade of this same standard. Degrease, dust off and remove rests of rust. Apply the required number of coatings to reach the recommended thickness level. Then apply the coats of finishing product, according to instructions. To be overcoated with two component enamels once the primer is thoroughly dry (24 hours), but always with application by spray-gun.

Other surfaces. Seek advice.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

For poorly adhered systems and/or showing rust, remove them by sandblasting up to Sa 2 ½ grade of the ISO 8501-2 standard or by means of manual or mechanical cleaning, up to ST3 grade of this same standard. Patch with the primer, preferably by brush.

Apply a whole coat of this primer and then the finishing product, according to specifications.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2018-09

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



TITAN

806 - SR RUST PREVENTIVE PRIMER 806

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

