

EXTRA OUTDOOR SYNTHETIC ENAMEL 813 SERVICOLOR BASE

Outdoors - Gloss. Clear



Product Code: 813 0597

Description

Base to be tinted with TITAN Servicolor System. It is an urethaned alkyd high gloss enamel with excellent retention of colour and good outdoor performance.

It has good elasticity, resistance to mineral oils and aliphatic hydrocarbons.

Fields of Application

As a general use finishing coat on steel and wood in industrial, rural and marine atmospheres with moderate chemical aggression.

For structural steel, iron gates, doors, etc., and for any iron and wooden surface, both in- or outdoors.

Technical Data

Product Type	Alkyd urethaned
Finish	Gloss
Colour (UNE EN ISO 11664-4)	Industrial SERVICOLOR Chart
Density (UNE EN ISO 2811-1)	0.92 - 0.94 Kg/l
Coverage (UNE 48282)	12 - 14 m ² /l (30 - 35 dry μ)
Drying at 23°C 60 % RH (UNE 48301)	4 hours
Recoat time at 23°C 60% RH (UNE 48283)	Mín. 18 hours
Methods of Application	Brush, Roller, Airless and Spray-gun.
Thinning	Brush and Roller: 5 % / Spray-gun: 10 % / Airless: -
Nozzle Diameter	Spray-gun 1.7 - 2.2 mm / Airless: 0.015" - 0.018" (the data quoted are only hints)
Nozzle Pressure	Spray-gun: 3 - 4 bar / Airless: 175 bar (The data quoted are only hints)
Thinner	875 Thinner
Equipment Cleaning	875 Thinner
Recommended Thickness (UNE EN ISO 2808)	70 - 100 dry μ in 2 or 3 coats
Application Temperature, RH<80%	+10°C - +30 °C
Maximal Volume Tinting Paste	12 - 12.5 %
Flash Point (UNE EN ISO 3679)	39 °C
Volume Solids (UNE EN ISO 3233-3)	41 - 48 %
Pack sizes	4 l and 750 ml. For 10 l a minimum order of 200 l is required

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Carefully stir the contents in the pack.

BARE SURFACES:

Steel: Previously apply one of the primers of our alkyd range, following directions for use and keeping the overcoating intervals. Then apply a suitable number of paint coats, depending on requirements.

Non ferrous metals: Previously apply one coat of 804 Primer or 871 Phosphatizing Wash Primer. To improve adhesion, some light sanding on metal may be necessary.

Other surfaces: Seek advice

The surfaces to be painted have to be clean, dry and sound.

In all cases:

Indoors: 1 - 2 coats (35 - 70 μ)

Outdoors: 2 - 3 coats (70 - 100 μ)

In order to improve the resistance to outdoor conditions, 3 enamel coats are recommended.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

If overcoating on well adhered systems, remove grease, oils and dirt (freshwater jet, thinner, etc.) Let to dry and apply one or two coats of paint, depending on requirements.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

If the previous paint system is badly adhered and/or has rust, it has to be removed by sandblasting up to Sa 2 ½ grade of the ISO 8501-1 standard or, alternatively, by hand or mechanical scraping or brushing up to ST-3 grade of this same standard. Then patch with the suitable primer, preferably by brush, and apply the required number of paint coats.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2018-05

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



TITAN

INDUSTRIAS TITAN S.A.U.
España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94
Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764



813 0597 - EXTRA OUTDOOR SYNTHETIC ENAMEL 813 SERVICOLOR BASE