

TITAN WHITENING PAINT 856

Indoors. Matt



Product Code: 856

Description

Soft odour water-based emulsion paint for painting walls and ceilings inside houses, industrial and business premises, etc. Very easy-to apply. Breathable. It does not alter the permeability of the surfaces. It permits the passage of water vapour through the painted surface.

Technical Data

| | |
|-----------------------------------------------|----------------------------------------|
| Product Type | Acrylic styrene |
| Finish | Matt |
| Colour (UNE EN ISO 11664-4) | White |
| Density (UNE EN ISO 2811-1) | 1.57 - 1.63 Kg/l |
| Coverage (UNE 48282) | 7 - 9 m ² /l |
| Drying at 23°C 60 % RH (UNE 48301) | 20 - 40 minutes |
| Recoat time at 23°C 60% RH (UNE 48283) | 6 - 8 hours |
| Methods of Application | Brush, roller and spray-gun. |
| Thinner | Water |
| Application Temperature, RH<80% | +10°C - +30°C |
| Volume Solids (UNE EN ISO 3233-3) | 42 - 43 % |
| VOC (UNE EN ISO 11890-2) | 2004/42/IIA (a) (75/30) Max. COV 5 g/l |
| Pack sizes | 25 Kg |

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Carefully stir the contents in the pack. The surfaces to be painted have to be clean, dry and sound.

BARE SURFACES:

If the surfaces are in good condition, apply a first coat thinned with 10 - 15% water., Apply a second unthinned coat.

If the surfaces are in poor condition, repair all the damaged areas, remove all poorly adhered particles and material. Clean all existing dirt and dust.

In order to homogenise porosity and improve the finish, as well as on distemper and size paints, whitewash or the surfaces where these have been removed, it is recommended to apply a first coat of A18 Water Based Sealing Primer or A19 Water Based Fixative.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

After washing or brushing the surface, directly apply a 10 - 15% water thinned first coat. Apply a second unthinned coat.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Thoroughly remove all previous paint coats and proceed as for bare surfaces.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Protect the packs from temperatures below 0°C

Issue date: 2017-09

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.

TITAN

856 - TITAN WHITENING PAINT 856

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

