

# FIXATIVE UNDERCOAT H10

Indoor - Outdoor



Product Code: H10

## Description

Water-based siloxane primer with high impregnation power. For indoor and outdoor application. Odourless. It allow the surface to breathe.

Fixative primer to seal surfaces which are highly absorbent, pulverulent, and with rests of previous paint in bad condition, highly burnt or with rests of old coats of low surface hardness, such as distemper paint, lime-based paints, plaster, etc.

Recommended fixative for H21 Waterproofing CoatingT with the aim of producing a breath-allowing, waterproof silicone system.

It improves paint adhesion on support. Moreover it avoids unevenness in the final finish because of irregular absorption areas.

In outdoor application, it improves waterproofness and resistance to rain.

Especially suitable for plaster which is to be painted for the first time in order to ensure consistency of the future paint coats.

## Technical Data

<b>Product Type</b>	Acrylic siliconed.
<b>Density (UNE EN ISO 2811-1)</b>	0.90 - 1.10 Kg/l
<b>Coverage (UNE 48282)</b>	2 - 5 m <sup>2</sup> /l
<b>Drying at 23°C 60 % RH (UNE 48301)</b>	20 - 30 minutes
<b>Recoat time at 23°C 60% RH (UNE 48283)</b>	4 - 6 hour
<b>Methods of Application</b>	Roller, brush and spray-gun.
<b>Thinner</b>	Water
<b>Application Temperature, RH&lt;80%</b>	+10°C - +30°C. Do not apply if rain is foreseen in the hours following application.
<b>Volume Solids (UNE EN ISO 3233-3)</b>	12.5 - 13.5%
<b>VOC (UNE EN ISO 11890-2)</b>	2004/42/IIA (h) (50/30) Mx. COV 0 g/l
<b>Pack sizes</b>	4 l and 750 ml

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

## Directions for use

### GENERAL REMARKS:

Carefully stir the contents in the pack. The surfaces to be painted have to be clean, dry and sound.

### BARE SURFACES:

For surfaces in poor condition, remove poorly adhered and loose particles before applying the product. Remove dirt and dust off. If the surfaces are very porous, apply a first coat thinned with 20 - 30% water. Before drying, apply a second unthinned coat.

## Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Protect the packs from temperatures below 0°C

Issue date: 2015-04

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.

# TITAN

H10 - FIXATIVE UNDERCOAT H10

### INDUSTRIAS TITAN S.A.U.

**España:** P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

**Portugal:** Rua Fonte Cova, 51 - 4475-031 Maia  
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia  
T. +351 229 865 450 - F. +351 229 810 764

