

TITANXYL WOODWORM TREATMENT PLUS

Indoor



Product Code: M56

Description

Ready-to-use wood protector TP08 for new and used wood and for class 1 use.

Class 1 use: indoor wood not exposed to weathering or humidity.

Protection :

Preventive against woodworm and termites.

Curative against woodworm.

Health Registration Number: ES-2019-08-00600-1

Fields of Application

For household and professional applications, such as for the protection of windows, doors, furniture, etc.

Technical Data

Colour (UNE EN ISO 11664-4)	Clear
Density (UNE EN ISO 2811-1)	1.01 Kg/l
Coverage (UNE 48282)	Prevention: 200 ml/m ² / Treatment: 300 ml/m ²
Drying at 23°C 60 % RH (UNE 48301)	1 hour
Recoat time at 23°C 60% RH (UNE 48283)	24 hours
Methods of Application	Brush and low pressure spray gun with unthinned product
Equipment Cleaning	Water and soap
Application Temperature, RH<80%	+10 °C - +30 °C
Pack sizes	4 l and 750 ml
Composition	Permethrin: 0.25% / Solvents and excipients q.s. 100%

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Certificates

Directions for use

GENERAL REMARKS:

Ready to use product. Do not thin. Carefully stir the contents in the pack.

The wood moisture content must not exceed 15%.

Tightly close the pack after use. Before applying TITANXYL Water Based Woodworm Treatment, protect the plastic items.

The woods to be treated have to be clean, dry and free from rotting and from any previous coat of varnish or paint in order to achieve their suitable impregnation with TITANXYL Water Based Woodworm Treatment.

Painted or varnished wood: Remove the existing coats entirely with TITAN Plus Paint Stripper and proceed as on new wood, after thoroughly cleaning away all traces of the Paint Stripper with dissolvent.

he product has to be applied only once every 5 years, if required.

BARE SURFACES:

Old unvarnished wood: It is essential to entirely remove the dried out, greyed surface by sanding or surfacing thoroughly until the wood in good condition is exposed. Then apply the Woodworm Treatment.

Resinous and tropical wood: Drying can be difficult. Clean the wooden surface with TITAN YATE Thinner. Apply one coat on a small area. Check if there is resin exudation. If this is the case, please refer to the Technical Service. If there is no exudation, finish with a suitable varnish or paint.

Wood attacked by woodworm: apply by injection until saturation, through the woodworm exit holes or for the drills made for this purpose.

Wood not attacked by woodworm: for preventive effect, apply TITANXYL Water Based Woodworm Treatment, by brush.

Always finish with a suitable varnish or paint.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

Waste management: Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use.

Safety interval: 24 hours. It must never be shorter than the time needed for surface drying.

Issue date: 2019-10

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products



TITAN

M56 - TITANXYL WOODWORM TREATMENT PLUS

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

