

## Descripción



Suitable for overcoating & retouching



Maximum certified washability Class 1



White to be tinted



Reaction to Fire



NULL

## Datos técnicos

Naturaleza	Vinyl versatate
Acabado	Extra Matt
Color (UNE EN ISO 11664-4)	White
Densidad (UNE EN ISO 2811-1)	1.56 - 1.62 Kg/l
Rendimiento	9 - 13 m <sup>2</sup> /l
Secado a 23°C 60 % HR (UNE 48301)	30
Repintado a 23°C 60% HR (UNE 48283)	8
Métodos de Aplicación	Brush, roller and airless
Viscosidad (UNE 48076)	110 - 125 KU
Diluyente	Water
Condiciones de Aplicación, HR<80%	+10°C - +30°C
Teñido	TITAN Universal Tinting Colours and Professional Water-Based Dye
Volumen Sólidos (UNE EN ISO 3233-3)	47.5 - 48.5 %
COV (UNE EN ISO 11890-2)	2.004/42/IIA (a) (75/30) Max. VOC 27 g/l
Presentación	15 l

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

## Certificaciones

Measure of antibacterial activity in plastics and other non-porous surfaces ISO 22196: R> 4.6. A surface is considered to have antibacterial activity if the R value is greater than or equal to 2

Wet-scrub resistance UNE EN ISO 11998: Class 1 washability

Reaction to Fire: UNE EN 13501-1: B-s1, d0 /on A2-s1, d0 surface

Determination of contrast ratio (Hiding Power) UNE EN ISO 6504-3: 8.30 m<sup>2</sup>/l, (98% coverage rate)  
VOC emission ISO 16000-6:2006: A+

### Modo de empleo

#### RECOMENDACIONES GENERALES:

Carefully stir the contents in the pack, manually or with low speed stirrer. The surfaces to be painted have to be clean, dry and sound. Do not apply on hot surfaces or in strong wind.

A good diagnosis and support preparation are essential for obtaining the best results.

#### SUPERFÍCIES NO PREPARADAS:

If the surfaces are in good condition, apply a first coat thinned with 10 - 15% water. Apply a second unthinned coat.

If the surfaces are in poor condition, repair all the damaged areas, remove all poorly adhered particles and material. Clean all existing dirt and dust.

In order to strengthen the surface and achieve uniform porosity, as well as on distemper and size paints, whitewash or surfaces where they have been removed, it is recommended to previously apply a base coat of S10 100% Acrylic All-Purpose Fixative or S50 Water-based Sealing Primer, following directions stated in the technical sheet.

#### MANTENIMIENTO SUPERFICIES YA PINTADAS EN BUEN ESTADO

Directly apply the paint after previous washing or brushing. Thin the first coat with 10 - 15% water. Apply a second unthinned coat.

#### MANTENIMIENTO SUPERFICIES YA PINTADAS EN MAL ESTADO

Thoroughly remove old paint coats and proceed as for bare surfaces.

### Precauciones

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

**Waste management:** Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use. Paint reuse can effectively minimize environmental effects on the life cycle of products.

Fecha de actualización: 2024-03

Toda Ficha Técnica queda anulada automáticamente por otra de fecha posterior o a los cinco años de su edición. Garantizamos la calidad de nuestros productos pero declinamos toda responsabilidad debida a factores ajenos a la pintura o a una utilización inadecuada de la misma. Ante cualquier duda consulte a nuestros servicios técnicos a priori.