

## Description

Silicone based acrylic coating for the decoration and protection of façades and single coat mortar. It provides hydrophobicity to the surface, thus increasing its resistance to rain water..



White to be tinted



Waterproof



Breathable



Great hardness and resistance

## Technical Data

Product Type	Acrylic styrene / silicone
Finish	Matt
Colour (UNE EN ISO 11664-4)	White
Density (UNE EN ISO 2811-1)	1.50 - 1.60 Kg/l
Coverage (UNE 48282)	6 - 8 m <sup>2</sup> /l (55 - 75 dry $\mu$ )
Drying at 23°C 60 % RH (UNE 48301)	20 - 40 minutes
Recoat time at 23°C 60% RH (UNE 48283)	6 - 8 hours
Methods of Application	Brush, roller and airless
Viscosity (UNE 48076)	125 - 135 KU
Thinner	Water.
Recommended Thickness (UNE EN ISO 2808)	110 - 147 dry $\mu$ in 2 coats
Application Temperature, RH<80%	+10°C - +30°C
Tinting	TITAN Universal Colourant or Water Based Professional Dye
Volume Solids (UNE EN ISO 3233-3)	43 -44%
VOC (UNE EN ISO 11890-2)	2.004/42/IIA (c) (75/40) Max. VOC 18 gr/l

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

## Certificates

Permeability to liquid water UNE EN 1062-3: W3 Waterproof  
Permeability to CO<sub>2</sub> UNE EN 1062-6: C1 Anticarbonation  
Permeability to water vapour UNE EN ISO 7783: Class 1. Breathable

### Directions for use

#### GENERAL REMARKS:

Carefully stir the contents in the pack, manually or with low speed stirrer. The surfaces to be painted have to be clean, dry and sound. Do not apply on hot surfaces or in strong wind. A good diagnosis and support preparation are essential for obtaining the best results.

#### BARE SURFACES:

Surfaces in good condition: Apply a first coat thinned with 10-15% water. Once dry, apply a second unthinned coat.

Surfaces in poor condition: Repair all the damaged areas. Remove all poorly adhered or inconsistent material. Get rid of dirt and existing dust.

In order to strengthen the surface and achieve uniform porosity, as well as on distemper and size paints, whitewash or surfaces where they were removed, it is recommended to previously apply a base coat of S10 100% Acrylic All Purpose Fixative Primer or S20 Acrylic High Impregnation Acrylic Fixative, following the directions stated in the technical sheet.

#### MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Directly apply the paint after previously having washed or brushed the surface. Apply a first coat thinned with 5% water and a second unthinned coat.

In the event that previously applied paint is not breathable, it has to be removed, so that the system can reach its optimum properties.

#### MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Thoroughly remove old paints and proceed as for bare surfaces.

### Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

**Waste management:** Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use.

Issue date: 2019-09

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.