

TITANLAK ENAMEL LACQUER

Indoor - Outdoor. Satin



Product Code: S02

Description

Premium quality and lacquered finish synthetic enamel. Excellent resistance to outdoor conditions, scratches, grease, water and detergents. It resists temperatures up to 90°C without damage.

Fields of Application

Suitable for decoration, DIY and handicrafts on wood, metal, cardboard, paper, stone, glass, ceramics and some plastics.

Technical Data

Product Type	Alkyd urethaned
Colour (UNE EN ISO 11664-4)	White and colour range
Coverage	200 ml spray can: 0.2 - 0.4 m ² , 400 ml spray can: 0.4 - 0.8 m ²
Drying at 23°C 60 % RH (UNE 48301)	3 - 4 hours
Recoat time at 23°C 60% RH (UNE 48283)	By 2 hours or after 24 hours
Application Temperature, RH<80%	+10°C - +30°C
Pack sizes	200 ml and 400 ml

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Shake the spray can for 1 minute after you begin to hear the mixing balls. The surfaces to be painted have to be clean, dry, degreased and rust free.

Apply crossed thin coats, at a distance of 25 - 30 cm. It is recommended to spray two thin coats instead of one single thick coat. In this way improved protection and a more homogeneous finish will be obtained.

Protect surfaces that are not to be painted. Perform a spray test on a non-visible area.

BARE SURFACES:

Apply one or two coats of Spray Rust-Preventive Primer or Spray Multi-Purpose Primer, depending on requirements. Finish with one or two coats of Spray Synthetic Enamel Lacquer. In order to achieve an excellent resistance to outdoor conditions, 3 coats of Spray Synthetic Enamel Lacquer are recommended.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Remove dust, grease or dirt and directly apply Spray Synthetic Enamel Lacquer.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Thoroughly remove all poorly adhered materials. Homogenise the surface by sanding. Once clean, rust-free and dry, proceed as for bare surfaces.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

Waste management: Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use.

Issue date: 2018-08

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



Akzo Nobel Coatings, S.L.U – Carrer Feixa Llarga, 14-20 - Pol. Ind. Zona Franca 08040 Barcelona
(Espanya)
Teléfono 934 842 500
Ins. Reg. Mer. de Barcelona T. 47631, F- 95, H. nº B-45052, Inscrp. 210
N.I.F. B-08218158



AkzoNobel

