

TITANLUX ALKYD VARNISH

Gloss



Product Code: S41

Description

High quality, gloss finish alkyd varnish. For decoration, DIY and handicrafts. To be applied on wood, cardboard, stone, glass, ceramics and some plastics. Excellent resistance to weathering, scratching and impacts.

Technical Data

Finish	Gloss
Colour (UNE EN ISO 11664-4)	Clear
Coverage (UNE 48282)	200 ml. can: 0.5 m ² / 400 ml. can: 1 m ²
Drying at 23°C 60 % RH (UNE 48301)	3 - 4 hours
Recoat time at 23°C 60% RH (UNE 48283)	24 hours.
Application Temperature, RH<80%	+10°C - +30°C
Pack sizes	400 ml and 200 ml

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Shake the spray for 1 minute after you begin to hear the mixing balls. The surfaces to be painted have to be clean, dry and sound.

Protect the surfaces that are not to be painted. Perform a spray test on a non-visible area.

Apply in crossed thin coats, at a distance of 25 - 30 cm. Apply two thin coats instead of one thick coat. Improved protection and a smoother finish will be achieved.

When applying the varnish on porous surfaces, such as baked clay, cardboard, dry flowers, some stones, etc. the gloss grade will be higher when applying even more varnish coats.

BARE SURFACES:

Apply a first coat. Once dry, sand it to remove typical wooden roughness, dust off and apply another coat of Universal Lacquer Varnish. Let to dry and apply, if required, a third coat.

When varnishing vegetal fibres, such as cane or wicker, it is necessary to carefully clean them with TITAN Odourless Thinner or TITAN White Spirit in order to remove wax and natural lubricants which could prevent adhesion. Once these fibres are dry, they can be varnished with Alkyd Varnish. In some cases, it is even more effective to lightly sand before cleaning with these solvents.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Remove dust, grease or dirt and lightly sand with moistened sandpaper (at least grade N^o. 320). Then apply TITANLUX Alkyd Varnish.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Thoroughly remove all poorly adhered materials. Smooth up the surface by sanding. Once clean, rust-free and dry, proceed as for bare surfaces.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2018-08

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.

TITAN

S41 - TITANLUX ALKYD VARNISH

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

