

PRIMER FOR GALVANIZED SURFACES

Indoor - Outdoor. Semi gloss



Product Code: S62

Description

Anticorrosive protection for surfaces made of galvanized iron and which are damaged by welding, sanding, holes, etc. It repairs the surface and adapts itself to the zinc-plated shade. Excellent anticorrosive protection also for any kind of steel surface.

Fields of Application

It can be used for protection against rust of welding joints, and mechanically damaged areas of iron tubes, galvanized sheets, etc., both in new and old items.

Technical Data

Product Type	Epoxy ester
Colour (UNE EN ISO 11664-4)	Grey and silver (similar to zinc-plated shade)
Coverage (UNE 48282)	400 ml. can: 1 m ²
Drying at 23°C 60 % RH (UNE 48301)	30 - 60 minutes
Recoat time at 23°C 60% RH (UNE 48283)	At least after 24 hours
Application Temperature, RH<80%	+10°C - +30°C
Pack sizes	400 ml

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Shake the spray can for 1 minute while hearing the mixing balls. The surfaces have to be clean, dry and free from grease and rust.

Apply by thin crossed coats from a distance of 25 to 30 cm.

It can be applied as a primer or as a final coat. Used as a primer, it can be overcoated after 24 hours with any of our TITAN Spray enamels.

Grey has a good thermic resistance, up to 250°C.

BARE SURFACES:

Remove rust with a wire brush or a sanding tool. Degrease, remove dust and rust residues.

Apply 1 or 2 coats depending on the environmental corrosion. Finish with any enamel of our Spray range.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Thoroughly remove old coats and proceed as for non-prepared surfaces.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2018-08

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.

TITAN

S62 - PRIMER FOR GALVANIZED SURFACES

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

