

# ACRITÓN SOLVENT FIXATIVE

Indoor - Outdoor



Product Code: TI500 21



## Description

Solution of special acrylic resins. Because of its high penetration and adhesion power, this product is suitable for priming and reinforcing dusty and unsound surfaces. It is also appropriate as a primer to improve adhesion on non-porous ceramic surfaces.

- \* Breathable. Air and water vapour can pass through the applied film.
- \* Water-insoluble flow.
- \* Excellent adhesion on concrete, brick, fibrocement and other materials currently used for building.
- \* Resistant to surface alkalinity and saltiness.
- \* High fixing power.
- \* Excellent penetration power.
- \* Quick-drying
- \* It resists rain.water from 20 min. after application, under normal conditions

## Fields of Application

Suitable for reinforcing surfaces which are deteriorated by time, such as cement mortar, plaster, concrete, brick... and for improving the consistency of roughcast, distemper paints and aged paints.

## Technical Data

<b>Product Type</b>	Special acrylic resins
<b>Finish</b>	Satin/Matt, depending on the surface absorption
<b>Colour (UNE EN ISO 11664-4)</b>	Colourless
<b>Density (UNE EN ISO 2811-1)</b>	0.82 - 0.84 Kg/l
<b>Coverage (UNE 48282)</b>	Plaster, size: 1.2 - 1.5 m <sup>2</sup> /l / Concrete, brick: 4 - 7 m <sup>2</sup> /l
<b>Drying at 23°C 60 % RH (UNE 48301)</b>	6 hours
<b>Recoat time at 23°C 60% RH (UNE 48283)</b>	24 hours
<b>Methods of Application</b>	Brush and roller
<b>Equipment Cleaning</b>	Clean the equipment with synthetics and grease thinner immediately after use
<b>Application Temperature, RH&lt;80%</b>	-20°C - +40°C. Do not apply if rain is foreseen in the following hours.
<b>Flash Point (UNE EN ISO 3679)</b>	37 °C
<b>Volume Solids (UNE EN ISO 3233-3)</b>	14 ± 1 %
<b>VOC (UNE EN ISO 11890-2)</b>	2.004/42/IIA (h) (750/750) Máx. COV 700 g/l
<b>Pack sizes</b>	5 l and 20 l

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

## Directions for use

### GENERAL REMARKS:

Thoroughly homogenise the content in the pack. The surface has to be dry and free from any dust, grease, saltpetre, mould, moss, etc.

Do not apply this product on asphaltic surfaces.

### BARE SURFACES:

Firstly, degrease the surface to be painted and remove the rests of concrete, sand, etc. by brushing. After removing all residues on the surface, apply one unthinned coat. If required, apply a second coat.

## Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Issue date: 2015-08

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



# TITAN

TI500 21 - ACRITÓN SOLVENTE FIXATIVE

### INDUSTRIAS TITAN S.A.U.

**España:** P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

**Portugal:** Rua Fonte Cova, 51 - 4475-031 Maia  
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia  
T. +351 229 865 450 - F. +351 229 810 764

