

## DESCRIPCIÓN

## DATOS TÉCNICOS

Naturaleza	Styrenated alkyd
Acabado	Matt
Color (UNE EN ISO 11664-4)	Black RAL 9011, Red RAL 3009, Grey RAL 7042, Blue RAL 5017 + Bases: 0597 Clear and 0599 White
Densidad (UNE EN ISO 2811-1)	1.41 - 1.55 Kg/l
Rendimiento	10 - 12 m <sup>2</sup> /l (30 - 35 dry microns)
Secado a 23°C 60 % HR (UNE 48301)	15 - 30 minutes
Repintado a 23°C 60% HR (UNE 48283)	Minimum: 2 hours
Métodos de Aplicación	Brush (Only for patching), Air Spray-Gun (The data quoted are only hints), Airless (The data quoted are only hints)
Dilucion	Brush: 0-5%, Air Spray-Gun: 10-15%, Airless: 3-5%
Diámetro Boquilla	Brush:--, Air Spray-Gun: 1.5 mm., Airless: 0.018-0.021
Presión Boquilla	Brush:--, Air Spray-Gun: 3-4 bar, Airless: 150 bar
Diluyente	875 or 872 Thinner (depending on room temperature)
Limpieza de Utensilios	875 or 872 Thinner (depending on room temperature)
Espesor Recomendado (UNE EN ISO 2808)	35 - 70 dry microns
Condiciones de Aplicación, HR<80%	+10°C - +30°C
Punto de Inflamación (UNE EN ISO 3679)	27 °C
Volumen Sólidos (UNE EN ISO 3233-3)	48 - 52 %
Presentación	Black: 4 l / Rest of colours: 15 l and 4 l / Bases: 15 and 4 l

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage

or in other properties.

## MODO DE EMPLEO

### RECOMENDACIONES GENERALES:

Carefully stir the product in the can.  
The surfaces to be painted have to be clean, dry and sound.

### SUPERFÍCIES NO PREPARADAS:

Steel: Remove rust by sandblasting up to Sa 2 ½ grade of the ISO 8501-1 standard or by means of manual or mechanical cleaning, up to ST3 grade of this same standard. Degrease, dust off and remove rests of rust. Apply the required number of coatings to reach the recommended thickness level. Then apply the coats of finishing product, according to instructions.  
Other surfaces. Seek advice.

### MANTENIMIENTO SUPERFÍCIES YA PINTADAS EN BUEN ESTADO

For poorly adhered systems and/or showing rust, remove them by sandblasting up to Sa 2 ½ grade of the ISO 8501-2 standard or by means of manual or mechanical cleaning, up to ST3 grade of this same standard. Patch with this primer, preferably by brush. Apply a whole coat of this primer and then the finishing product, according to specifications.  
If there is a large poorly adhered surface, thoroughly remove old coats and proceed as for bare surfaces.

## PRECAUCIONES

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.  
Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.  
Waste management: Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use. Paint reuse can effectively minimize environmental effects on the life cycle of products.

Fecha de actualización : 2021-05

Toda Ficha Técnica queda anulada automáticamente por otra de fecha posterior o a los cinco años de su edición. Garantizamos la calidad de nuestros productos pero declinamos toda responsabilidad debida a factores ajenos a la pintura o a una utilización inadecuada de la misma. Ante cualquier duda consulte a nuestros servicios técnicos a priori.