

## DESCRIPCIÓN

## DATOS TÉCNICOS

Naturaleza	Alkyd
Acabado	Matt
Color (UNE EN ISO 11664-4)	Red, Grey, 0597 Clear Base and 0599 White Base
Densidad (UNE EN ISO 2811-1)	1,22 - 1,28 Kg/l
Rendimiento	9 - 11 m <sup>2</sup> /l (35 - 40 dry $\mu$ )
Secado a 23°C 60 % HR (UNE 48301)	15 - 30 min.
Repintado a 23°C 60% HR (UNE 48283)	Minimum: 2 hours. Maximum: 15 days / Polyurethane, epoxy and chlorinated rubber: 48 hours
Métodos de Aplicación	Brush and roller (Only for patching), Air Spray-Gun and Airless (The data quoted are only hints)
Dilucion	Brush: 5 - 10%, Air Spray-Gun: 10 - 15%, Airless: 0 - 5%
Diámetro Boquilla	Air Spray-Gun: 1.5 mm, Airless: 0.018" - 0.021"
Presión Boquilla	Air Spray-Gun: 3 - 4 bar, Airless: 150 bar
Diluyente	872 and 875 Thinner
Limpieza de Utensilios	872 and 875 Thinner
Espesor Recomendado (UNE EN ISO 2808)	40 - 80 dry $\mu$
Condiciones de Aplicación, HR<80%	+10°C - +30°C
Punto de Inflamación (UNE EN ISO 3679)	27 °C
Volumen Sólidos (UNE EN ISO 3233-3)	37 - 39 %
Presentación	Grey: 10 l and 4 l, Red: 4 l / Bases: 4 l and 750 ml

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

## MODO DE EMPLEO

### RECOMENDACIONES GENERALES:

Carefully stir the product in the pack. The surfaces to be painted have to be clean, dry and sound. The minimum interval for overcoating polyurethane, epoxy and chlorinated rubber is 48 hours.

### SUPERFÍCIES NO PREPARADAS:

Steel: Remove rust by sandblasting up to Sa 2 ½ grade of the ISO 8501-1 standard or by means of manual or mechanical cleaning, up to ST-3 grade of this same standard. Degrease, dust off and remove rests of rust. Apply the required number of coats to reach the recommended thickness level. Then apply the coats of finishing product, according to instructions.

Other surfaces: Seek advice.

### MANTENIMIENTO SUPERFÍCIES YA PINTADAS EN BUEN ESTADO

For poorly adhered systems and/or showing rust, remove them by sandblasting up to Sa 2 ½ grade of the ISO 8501-2 standard or by means of manual or mechanical cleaning, up to ST-3 grade of this same standard. Patch with this primer, preferably by brush. Apply a full coat of this primer and then the finishing product, according to specifications.

If there is a large poorly adhered surface, thoroughly remove old coats and proceed as for bare surfaces.

## PRECAUCIONES

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

Waste management: Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use. Paint reuse can effectively minimize environmental effects on the life cycle of products.

Fecha de actualización : 2021-05

Toda Ficha Técnica queda anulada automáticamente por otra de fecha posterior o a los cinco años de su edición. Garantizamos la calidad de nuestros productos pero declinamos toda responsabilidad debida a factores ajenos a la pintura o a una utilización inadecuada de la misma. Ante cualquier duda consulte a nuestros servicios técnicos a priori.