

DESCRIPCIÓN

DATOS TÉCNICOS

Naturaleza	Alkyd
Acabado	Satin
Color (UNE EN ISO 11664-4)	Red and grey.
Densidad (UNE EN ISO 2811-1)	1.35 - 1.45 Kg/l
Rendimiento	12 - 14 m ² /l (35 - 40 dry μ)
Secado a 23°C 60 % HR (UNE 48301)	2 - 3 hours
Repintado a 23°C 60% HR (UNE 48283)	18 hours
Métodos de Aplicación	Brush, Roller, Air Spray-Gun and Airless
Dilucion	Brush and roller: 0 - 5%, Air Spray-Gun: 10 - 15%, Airless: 0 -5% (The data quoted are only hints)
Diámetro Boquilla	Air Spray-Gun: 1.5 mm., Airless: 0.018" - 0.021"
Limpieza de Utensilios	872 or 875 Thinner (depending on environment)
Espesor Recomendado (UNE EN ISO 2808)	40 - 80 dry μ
Condiciones de Aplicación, HR<80%	+10°C - +30°C
Punto de Inflamación (UNE EN ISO 3679)	43°C
Volumen Sólidos (UNE EN ISO 3233-3)	54 - 56 %
Presentación	Red. 10l and 4l / Grey: 4l and 750 ml.

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

MODO DE EMPLEO

RECOMENDACIONES GENERALES:

Carefully stir the product in the pack. The surfaces to be painted have to be clean, dry and sound.

Finish with any of our alkyd enamels. For topcoats with polyurethane, epoxy and chlorinated-rubber, the minimum overcoating interval is 48 hours.

SUPERFÍCIES NO PREPARADAS:

Steel: Remove rust by sandblasting up to Sa 2 ½ grade of the ISO 8501-1 standard or by means of manual or mechanical cleaning, up to ST3 grade of this same standard. Degrease, dust off and remove rests of rust. Apply the required number of coatings to reach the recommended thickness level. Then apply the coats of finishing product, according to instructions.

Other surfaces. Seek advice.

MANTENIMIENTO SUPERFICIES YA PINTADAS EN MAL ESTADO

For poorly adhered systems and/or showing rust, remove them by sandblasting up to Sa 2 ½ grade of the ISO 8501-2 standard or by means of manual or mechanical cleaning, up to ST3 grade of this same standard. Degrease, dust off and remove rests of rust. Patch with this primer, preferably by brush. Apply a whole coat of this primer and then the finishing product, according to specifications.

If there is a large poorly adhered surface, thoroughly remove old coats and proceed as for bare surfaces.

PRECAUCIONES

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

Waste management: Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use. Paint reuse can effectively minimize environmental effects on the life cycle of products.

Fecha de actualización : 2021-05

Toda Ficha Técnica queda anulada automáticamente por otra de fecha posterior o a los cinco años de su edición. Garantizamos la calidad de nuestros productos pero declinamos toda responsabilidad debida a factores ajenos a la pintura o a una utilización inadecuada de la misma. Ante cualquier duda consulte a nuestros servicios técnicos a priori.