

## DESCRIPCIÓN

## DATOS TÉCNICOS

Naturaleza	Vinyl
Acabado	Matt
Color (UNE EN ISO 11664-4)	White and Grey
Densidad (UNE EN ISO 2811-1)	1.37-1.45 Kg/l
Rendimiento	8-12 m <sup>2</sup> /l (30 - 35 dry microns)
Secado a 23°C 60 % HR (UNE 48301)	30 - 60 minutes
Repintado a 23°C 60% HR (UNE 48283)	2 hours.For two components products 24 hours.
Métodos de Aplicación	Brush, Air spray-gun and Airless
Dilucion	Brush: 5%, Air spray-gun: 10-15%, Airless: 0-5% (the data quoted are only hints)
Diámetro Boquilla	Air spray-gun: 1.5 mm, Airless: 0.018
Presión Boquilla	Air spray-gun: 3 - 4 bar, Airless: 150 bar (the data quoted are only hints)
Diluyente	872 or 878 Thinner (depending on room temperature)
Limpieza de Utensilios	872 or 878 Thinner (depending on room temperature)
Espesor Recomendado (UNE EN ISO 2808)	Non- ferrous metal: 30 - 35 dry microns (one coat), Ferrous metal: 70 - 80 dry microns (2 coats)
Condiciones de Aplicación, HR<80%	+10°C - + 30°C
Punto de Inflamación (UNE EN ISO 3679)	27°C
Volumen Sólidos (UNE EN ISO 3233-3)	42 - 46 %
COV (UNE EN ISO 11890-2)	2.004/42IIA (i) (600/500) Max. COV 500 g/l

Presentación

4l and 10l

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

## MODO DE EMPLEO

### RECOMENDACIONES GENERALES:

Carefully stir the product in the pack. The surfaces to be painted have to be clean, dry and sound.

### SUPERFÍCIES NO PREPARADAS:

Iron: Remove rust by sandblasting up to Sa 2 ½ grade of the ISO 8501-1 standard or by means of manual or mechanical cleaning, up to ST3 grade of this same standard. Degrease, dust off and remove rests of rust. Apply the required number of coatings to reach the recommended thickness level. Then apply the coats of finishing product, according to instructions.

Galvanised steel or non-ferrous metals: Clean and degrease and apply one coat of the primer. Depending quality of galvanised steel, open pores is necessary

Other surfaces. Seek advice

### MANTENIMIENTO SUPERFICIES YA PINTADAS EN MAL ESTADO

For poorly adhered systems and/or showing rust, remove them by sandblasting up to Sa 2 ½ grade of the ISO 8501-2 standard or by means of manual or mechanical cleaning, up to ST3 grade of this same standard. Degrease, dust off and remove rests of rust. Patch with this primer, preferably by brush. Apply a whole coat of this primer and then the finishing product, according to specifications.

## PRECAUCIONES

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

Waste management: Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use. Paint reuse can effectively minimize environmental effects on the life cycle of products.

Fecha de actualización: 2024-03

Toda Ficha Técnica queda anulada automáticamente por otra de fecha posterior o a los cinco años de su edición. Garantizamos la calidad de nuestros productos pero declinamos toda responsabilidad debida a factores ajenos a la pintura o a una utilización inadecuada de la misma. Ante cualquier duda consulte a nuestros servicios técnicos a priori.