

DESCRIPCIÓN

DATOS TÉCNICOS

Naturaleza	Cyclized rubber
Acabado	Satin
Color (UNE EN ISO 11664-4)	Typical metallic grey
Densidad (UNE EN ISO 2811-1)	2.80 - 3.00 Kg/l
Rendimiento	9 - 10 m ² /l (50 - 55 dry μ)
Secado a 23°C 60 % HR (UNE 48301)	30 - 60 minutes
Repintado a 23°C 60% HR (UNE 48283)	6 - 8 hours
Métodos de Aplicación	Brush and roller (Just for patching), Air Spray-Gun , Airless (The data quoted are only hints)
Dilucion	Brush and roller: 0 - 5%, Air Spray-Gun: Max.10%, Airless: 0 - 5%
Diámetro Boquilla	Air Spray-Gun: 1.7 - 2.2 mm., Airless: 0.018" - 0.022"
Diluyente	875 Thinner
Limpieza de Utensilios	875 Thinner
Espesor Recomendado (UNE EN ISO 2808)	50 - 55 dry μ
Condiciones de Aplicación, HR<80%	+10°C - +30°C
Punto de Inflamación (UNE EN ISO 3679)	38°C
Volumen Sólidos (UNE EN ISO 3233-3)	60% in Zinc
Presentación	4 l and 750 ml. For 10 l, a minimum order of 200 l is required.

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

MODO DE EMPLEO

RECOMENDACIONES GENERALES:

Carefully stir the product in the pack. The surfaces to be painted have to be clean, dry and sound. It can be overcoated with our Alkyd or Chlorinated Rubber Enamels, depending on requirements. If the finishing coat is applied some days after the primer, it will be necessary to clean the surface and remove the white salts that might have appeared on the surface.

SUPERFÍCIES NO PREPARADAS:

Steel: When it is exposed to atmospheres with moderate chemical aggression, scour with mechanic brush up to ST-3 of the ISO Standard 8501-1. In corrosive atmospheres steel has to be shot blasted until Sa-2 of the above mentioned Standard. The surface needs a medium roughness corresponding to grade BN9 of the N3 roughness test. After that apply a coat of Galvanised Primer 803 and the required number of coats of the finishing product following the directions given.

MANTENIMIENTO SUPERFICIES YA PINTADAS EN BUEN ESTADO

Because of the peculiar characteristics of this primer, among which the physical contact with the ferrous substrate is essential, we recommend, when possible, to completely remove the previous coats with mechanical procedures up to level ST-3 minimum grade. After that apply a coat of Galvanised Primer 803 and the finishing product following the directions given.

PRECAUCIONES

Always read the pack label before use. For more information, please refer to the Safety Data Sheet. Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.
Waste management: Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use. Paint reuse can effectively minimize environmental effects on the life cycle of products.

Fecha de actualización : 2021-05

Toda Ficha Técnica queda anulada automáticamente por otra de fecha posterior o a los cinco años de su edición. Garantizamos la calidad de nuestros productos pero declinamos toda responsabilidad debida a factores ajenos a la pintura o a una utilización inadecuada de la misma. Ante cualquier duda consulte a nuestros servicios técnicos a priori.