

DESCRIPCIÓN

DATOS TÉCNICOS

Naturaleza	Alkyd urethaned
Acabado	Gloss
Color (UNE EN ISO 11664-4)	White and colours + 0597 Clear Base and 0599 White Base
Densidad (UNE EN ISO 2811-1)	0,95 - 1,26 Kg/l
Rendimiento	12 - 14 m ² /l (30 - 35 μ dry microns)
Secado a 23°C 60 % HR (UNE 48301)	4 hours
Repintado a 23°C 60% HR (UNE 48283)	Minimum: 18 hours
Métodos de Aplicación	Brush, Roller, Airless and Spray-gun
Dilucion	Brush and Roller: 5 % / Spray-gun: 10 % / Airless: -
Diámetro Boquilla	Spray-gun 1.7 - 2.2 mm / Airless: 0,015" - 0.018" (the data quoted are only hints)
Presión Boquilla	Spray-gun: 3 - 4 bar / Airless: 175 bar (The data quoted are only hints)
Diluyente	875 Thinner
Limpieza de Utensilios	875 Thinner
Espesor Recomendado (UNE EN ISO 2808)	70 - 100 μ dry μ in 2 or 3 coats
Condiciones de Aplicación, HR<80%	+10 °C - +30 °C
Punto de Inflamación (UNE EN ISO 3679)	39 °C
Volumen Sólidos (UNE EN ISO 3233-3)	41 - 48 %
Presentación	4 l / Bases.- Clear: 10 l, 4 l and 750 ml, White: 4 l and 750 ml

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage

or in other properties.

CERTIFICACIONES

Reaction to Fire UNE EN 13501-1: 2007 + A1: 2010: B-s1, d0

MODO DE EMPLEO

RECOMENDACIONES GENERALES:

- Carefully stir the contents in the pack.
- The surfaces to be painted have to be clean, dry and sound.

SUPERFÍCIES NO PREPARADAS:

- Steel: Previously apply one of the primers of our alkyd range, following directions for use and keeping the overcoating intervals. Then apply a suitable number of paint coats, depending on requirements.
- Non ferrous metals: Previously apply one coat of 804 or 871 Primer. To improve adhesion, some light sanding on metal may be necessary.
- Other surfaces: Seek advice
- In all cases
- Indoors: 1 - 2 coats (35 - 70 μ)
- Outdoors: 2 - 3 coats (70 - 100 μ)
- In order to improve the resistance to outdoor conditions, 3 enamel coats are recommended.

MANTENIMIENTO SUPERFICIES YA PINTADAS EN BUEN ESTADO

If overcoating on well adhered systems, remove grease, oils and dirt (freshwater jet, thinner, etc.) Let to dry and apply one or two coats of paint, depending on requirements.

MANTENIMIENTO SUPERFICIES YA PINTADAS EN MAL ESTADO

If the previous paint system is badly adhered and/or has rust, it has to be removed by sandblasting up to Sa 2 1/2 grade of the ISO 8501-1 standard or, alternatively, by hand or mechanical scraping or brushing up to ST-3 grade of this same standard. Then patch with the suitable primer, preferably by brush, and apply the required number of paint coats.

PRECAUCIONES

Always read the pack label before use. For more information, please refer to the Safety Data Sheet. Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

Waste management: Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use. Paint reuse can effectively minimize environmental effects on the life cycle of products.

Fecha de actualización: 2023-05

Toda Ficha Técnica queda anulada automáticamente por otra de fecha posterior o a los cinco años de su edición. Garantizamos la calidad de nuestros productos pero declinamos toda responsabilidad debida a factores ajenos a la pintura o a una utilización inadecuada de la misma. Ante cualquier duda consulte a nuestros servicios técnicos a priori.