

DESCRIPCIÓN

DATOS TÉCNICOS

Naturaleza	100% Acrylic
Acabado	Gloss
Brillo (UNE EN ISO 2813)	60° >90%
Color (UNE EN ISO 11664-4)	0566 White Base + 0597 Clear Base
Densidad (UNE EN ISO 2811-1)	White Base: 1.10 - 1.12 / Clear Base: 0.96 - 0.98
Rendimiento	8 - 10 m ² /l (30 - 35μ)
Secado a 23°C 60 % HR (UNE 48301)	30 - 60 minutes
Repintado a 23°C 60% HR (UNE 48283)	After 4 hours
Métodos de Aplicación	Roller and spray-gun (brush, only for patching)
Dilucion	0 - 5%. Application by air spray-gun may require up to 15% thinning.
Diámetro Boquilla	Air spray-gun: 1.5 mm / Airless: 0.015" - 0.018"
Diluyente	DX800 Chlorinated Rubber / Acrylic Thinner, DX820 Polyurethane Thinner or DX840 Multi Purpose Thinner
Limpieza de Utensilios	DX800 Chlorinated Rubber / Acrylic Thinner or DX840 Multi Purpose Thinner
Espesor Recomendado (UNE EN ISO 2808)	30 - 35 μ
Condiciones de Aplicación, HR<80%	0°C - +30°C
Teñido	Industrial TITANCOLOR System
Vol.máx pasta colorante	White base: 5% / Clear base: 12.5%
Punto de Inflamación (UNE EN ISO 3679)	27°C

Volumen Sólidos (UNE EN ISO 3233-3)	31 - 33%
COV (UNE EN ISO 11890-2)	595 - 600 g/l
Presentación	15 l and 4 l

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

MODO DE EMPLEO

RECOMENDACIONES GENERALES:

Thoroughly stir the contents in the pack. Surfaces to be painted have to be clean, dry and in good condition. Avoid applying too thick coats since this can lead to blisters caused by solvent retention.

SUPERFÍCIES NO PREPARADAS:

Steel: previously apply DTM SX150 Acrylic Primer according to specifications and observing the overcoating intervals. Finish with a coat of enamel. Unsaponifiable formula that can be used as a top coat over SX160 Galvanic Gray Primer SX160 with High Zinc Content.

Non-ferrous metals: previously apply DTM SX150 Acrylic Primer according to specifications.

Other supports: Seek advice.

MANTENIMIENTO SUPERFICIES YA PINTADAS EN BUEN ESTADO

In case of repainting on well adhered systems, remove any grease, oil and dirt (fresh water jet, solvent, etc.) and then let it dry. Finish with a coat of enamel.

MANTENIMIENTO SUPERFICIES YA PINTADAS EN MAL ESTADO

In the case of poorly adhered systems, and / or with the presence of rust, remove by abrasive blasting up to the degree Sa2½ of the ISO 8501-2 standard or manual or mechanical cleaning up to the ST3 grade of the same standard. Patch the bare areas with DTM SX150 Acrylic Primer, preferably by brush to the specified thickness and a topcoat of HP EX400 Acrylic Enamel

PRECAUCIONES

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

Waste management: Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points. Calculate the amount of product you will need to avoid waste and extra costs. Collect the leftover material and keep it well stored for a new use. Paint reuse can effectively minimize environmental effects on the life cycle of products.

Fecha de actualización : 2021-05

Toda Ficha Técnica queda anulada automáticamente por otra de fecha posterior o a los cinco años de su edición. Garantizamos la calidad de nuestros productos pero declinamos toda responsabilidad debida a factores ajenos a la pintura o a una utilización inadecuada de la misma. Ante cualquier duda consulte a nuestros servicios técnicos a priori.